




# OIL ANALYSIS REPORT

Sample Rating Trend

**NORMAL**



Machine Id

**454M**

Component

**Diesel Engine**

Fluid

**PETRO CANADA DURON SHP 15W40 (5 GAL)**

## DIAGNOSIS

### Recommendation

Resample at the next service interval to monitor. ( Customer Sample Comment: Early sampled )

### Wear

All component wear rates are normal.

### Contamination

There is no indication of any contamination in the oil.

### Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

## SAMPLE INFORMATION

	method	limit/base	current	history1	history2
Sample Number	Client Info		<b>GFL0115076</b>	GFL0097678	---
Sample Date	Client Info		<b>26 Mar 2024</b>	09 Jan 2024	---
Machine Age	hrs	Client Info	<b>14842</b>	28478	---
Oil Age	hrs	Client Info	<b>0</b>	600	---
Oil Changed	Client Info		<b>Not Chngd</b>	Changed	---
Sample Status			<b>NORMAL</b>	NORMAL	---

## CONTAMINATION

	method	limit/base	current	history1	history2
Fuel	WC Method	>3.0	<b>&lt;1.0</b>	<1.0	---
Water	WC Method	>0.2	<b>NEG</b>	NEG	---
Glycol	WC Method		<b>NEG</b>	NEG	---

## WEAR METALS

	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m >90	<b>1</b>	36	---
Chromium	ppm	ASTM D5185m >20	<b>&lt;1</b>	2	---
Nickel	ppm	ASTM D5185m >2	<b>0</b>	<1	---
Titanium	ppm	ASTM D5185m >2	<b>0</b>	0	---
Silver	ppm	ASTM D5185m >2	<b>0</b>	0	---
Aluminum	ppm	ASTM D5185m >20	<b>&lt;1</b>	4	---
Lead	ppm	ASTM D5185m >40	<b>0</b>	0	---
Copper	ppm	ASTM D5185m >330	<b>0</b>	2	---
Tin	ppm	ASTM D5185m >15	<b>0</b>	0	---
Vanadium	ppm	ASTM D5185m	<b>0</b>	<1	---
Cadmium	ppm	ASTM D5185m	<b>0</b>	0	---

## ADDITIVES

	method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m 0	<b>2</b>	2	---
Barium	ppm	ASTM D5185m 0	<b>0</b>	0	---
Molybdenum	ppm	ASTM D5185m 60	<b>55</b>	67	---
Manganese	ppm	ASTM D5185m 0	<b>&lt;1</b>	<1	---
Magnesium	ppm	ASTM D5185m 1010	<b>917</b>	1142	---
Calcium	ppm	ASTM D5185m 1070	<b>1011</b>	1208	---
Phosphorus	ppm	ASTM D5185m 1150	<b>1042</b>	1185	---
Zinc	ppm	ASTM D5185m 1270	<b>1210</b>	1501	---
Sulfur	ppm	ASTM D5185m 2060	<b>3492</b>	3460	---

## CONTAMINANTS

	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m >25	<b>3</b>	7	---
Sodium	ppm	ASTM D5185m	<b>&lt;1</b>	16	---
Potassium	ppm	ASTM D5185m >20	<b>&lt;1</b>	12	---

## INFRA-RED




	method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844 >6	<b>0.1</b>	0.7	---
Nitration	Abs/cm	*ASTM D7624 >20	<b>4.8</b>	9.9	---
Sulfation	Abs/.1mm	*ASTM D7415 >30	<b>17.6</b>	21.6	---

## FLUID DEGRADATION

	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414 >25	<b>13.3</b>	19.0	---
Base Number (BN)	mg KOH/g	ASTM D2896 9.8	<b>9.1</b>	9.0	---







# OIL ANALYSIS REPORT



VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	---
Yellow Metal	scalar	*Visual	NONE	NONE	---
Precipitate	scalar	*Visual	NONE	NONE	---
Silt	scalar	*Visual	NONE	NONE	---
Debris	scalar	*Visual	NONE	NONE	---
Sand/Dirt	scalar	*Visual	NONE	NONE	---
Appearance	scalar	*Visual	NORML	NORML	---
Odor	scalar	*Visual	NORML	NORML	---
Emulsified Water	scalar	*Visual	>0.2	NEG	---
Free Water	scalar	*Visual		NEG	---

FLUID PROPERTIES	method	limit/base	current	history1	history2
Visc @ 100°C	cSt	ASTM D445	15.4	<b>14.3</b>	15.1

## GRAPHS



**Laboratory** : WearCheck USA - 501 Madison Ave., Cary, NC 27513  
**Sample No.** : GFL0115076      **Received** : 02 Apr 2024  
**Lab Number** : **06136098**      **Tested** : 03 Apr 2024  
**Unique Number** : 10955563      **Diagnosed** : 04 Apr 2024 - Don Baldrige  
**Test Package** : FLEET

**GFL Environmental - 405 - Arbor Hills**  
 7811 Chubb Rd  
 NORTHVILLE, MI  
 US 48168  
 Contact: Anthony Hopkins  
 ahopkins@gflenv.com  
 T:  
 F:

To discuss this sample report, contact Customer Service at 1-800-237-1369.  
 \* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.  
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)