

## **OIL ANALYSIS REPORT**

Sample Rating Trend

-----



923036-205290 Diesel Engine

Machine Id

PETRO CANADA DURON SHP 15W40 (--- LTR)

			Apr2022	NOVZUZZ Apr2023		1ar2024	
DIAGNOSIS	SAMPLE INFOF	RMATION	method	limit/base	current	history1	history2
Recommendation	Sample Number		Client Info		GFL0109243	GFL0109321	GFL0093570
Resample at the next service interval to monitor.	Sample Date		Client Info		01 Apr 2024	07 Mar 2024	29 Jan 2024
Wear	Machine Age	hrs	Client Info		4989	4825	4689
All component wear rates are normal.	Oil Age	hrs	Client Info		531	367	231
Contamination	Oil Changed		Client Info		Not Changd	Not Changd	Not Changd
There is no indication of any contamination in the	Sample Status				NORMAL	NORMAL	NORMAL
oil.	CONTAMINAT	ΓΙΟΝ	method	limit/base	current	history1	history2
Fluid Condition	Fuel		WC Method	>3.0	<1.0	<1.0	<1.0
The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the	Water		WC Method	>0.2	NEG	NEG	NEG
oil is suitable for further service.	Glycol		WC Method		NEG	NEG	NEG
	WEAR METAL	_S	method	limit/base	current	history1	history2
	Iron	ppm	ASTM D5185m	>120	9	6	6
	Chromium	ppm	ASTM D5185m	>20	0	0	<1
	Nickel	ppm	ASTM D5185m		4	3	2
	Titanium	ppm	ASTM D5185m	>2	49	44	50
	Silver	ppm	ASTM D5185m	>2	0	0	0
	Aluminum	ppm	ASTM D5185m	>20	2	2	2
	Lead	ppm	ASTM D5185m		0	0	<1
	Copper	ppm	ASTM D5185m	>330	9	7	8
	Tin	ppm	ASTM D5185m		0	<1	<1
	Vanadium	ppm	ASTM D5185m		<1	<1	<1
	Cadmium	ppm	ASTM D5185m		0	0	0
	ADDITIVES		method	limit/base	current	history1	history2
	Boron	ppm	ASTM D5185m	0	24	34	61
	Barium	ppm	ASTM D5185m	0	0	0	0
	Molybdenum	ppm	ASTM D5185m	60	31	27	29
	Manganese	ppm	ASTM D5185m	0	0	<1	0
	Magnesium	ppm	ASTM D5185m	1010	693	669	633
	Calcium	ppm	ASTM D5185m	1070	1504	1312	1380
	Phosphorus	ppm	ASTM D5185m	1150	982	959	893
	Zinc	ppm	ASTM D5185m	1270	1257	1202	1158
	Sulfur	ppm	ASTM D5185m	2060	3611	3118	3610
	CONTAMINAN	NTS	method	limit/base	current	history1	history2
	Silicon	ppm	ASTM D5185m	>25	4	5	4
	Sodium	ppm	ASTM D5185m		11	8	1
	Potassium	ppm	ASTM D5185m	>20	4	5	4
	INFRA-RED		method	limit/base	current	history1	history2
	Soot %	%	*ASTM D7844	>4	0.1	0.1	0.1
	Nitration	Abs/cm	*ASTM D7624	>20	8.7	8.4	7.5
	Sulfation	Abs/.1mm	*ASTM D7415	>30	21.6	20.3	19.0
	FLUID DEGRA	DATION	method	limit/base	current	history1	history2
	Oxidation	Abs/.1mm	*ASTM D7414	>25	18.4	16.7	15.3
	<b>D</b>						

Base Number (BN) mg KOH/g ASTM D2896 9.8


6.7


6.3

5.7




## **OIL ANALYSIS REPORT**





VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	LIGHT
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG
FLUID PROPE	RTIES	method	limit/base	current	history1	history2
Visc @ 100°C	cSt	ASTM D445	15.4	13.7	13.8	14.0

GRAPHS



Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Certificate L2367