


OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL



Machine Id
PETERBILT 150-13
 Component
Diesel Engine
 Fluid
PETRO CANADA DURON SHP 15W40 (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

SAMPLE INFORMATION		method	limit/base	current	history1	history2
Sample Number	Client Info			PCA0114639	PCA0089565	PCA0070768
Sample Date	Client Info			06 Mar 2024	25 Jan 2024	05 Aug 2022
Machine Age	mls	Client Info		0	0	369000
Oil Age	mls	Client Info		4000	10000	10000
Oil Changed	Client Info			Changed	Changed	Changed
Sample Status				NORMAL	NORMAL	NORMAL

CONTAMINATION		method	limit/base	current	history1	history2
Fuel	WC Method	>5		<1.0	<1.0	<1.0
Water	WC Method	>0.2		NEG	NEG	NEG
Glycol	WC Method			NEG	NEG	NEG

WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>100	4	16	57
Chromium	ppm	ASTM D5185m	>20	0	<1	2
Nickel	ppm	ASTM D5185m	>2	0	0	0
Titanium	ppm	ASTM D5185m	>2	<1	0	<1
Silver	ppm	ASTM D5185m	>2	0	0	0
Aluminum	ppm	ASTM D5185m	>25	1	2	2
Lead	ppm	ASTM D5185m	>40	0	<1	3
Copper	ppm	ASTM D5185m	>330	<1	2	4
Tin	ppm	ASTM D5185m	>15	0	<1	<1
Vanadium	ppm	ASTM D5185m		<1	0	0
Cadmium	ppm	ASTM D5185m		0	0	<1




ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	0	3	3	10
Barium	ppm	ASTM D5185m	0	0	2	2
Molybdenum	ppm	ASTM D5185m	60	59	51	62
Manganese	ppm	ASTM D5185m	0	0	0	<1
Magnesium	ppm	ASTM D5185m	1010	1033	835	880
Calcium	ppm	ASTM D5185m	1070	1085	927	1178
Phosphorus	ppm	ASTM D5185m	1150	1092	907	1051
Zinc	ppm	ASTM D5185m	1270	1312	1094	1278
Sulfur	ppm	ASTM D5185m	2060	3946	2832	3043

CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	2	4	5
Sodium	ppm	ASTM D5185m		2	3	5
Potassium	ppm	ASTM D5185m	>20	<1	2	5

INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844	>3	0.2	0.3	1.8
Nitration	Abs/cm	*ASTM D7624	>20	5.5	7.5	11.0
Sulfation	Abs/.1mm	*ASTM D7415	>30	17.8	19.0	24.6

FLUID DEGRADATION		method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414	>25	13.7	14.8	18.8
Base Number (BN)	mg KOH/g	ASTM D2896	9.8	9.2	9.0	10.2









OIL ANALYSIS REPORT



PARAMETER	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG

FLUID PROPERTIES	method	limit/base	current	history1	history2	
Visc @ 100°C	cSt	ASTM D445	15.4	14.3	12.8	15.3

GRAPHS



Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : PCA0114639 **Received** : 04 Apr 2024
Lab Number : **06138334** **Tested** : 05 Apr 2024
Unique Number : 10963142 **Diagnosed** : 05 Apr 2024 - Wes Davis
Test Package : MOB 1 (Additional Tests: TBN)

GE MARSHALL EXCAVATION
 1351 JOLIET RD
 VALPARAISO, IN
 US 46385
 Contact: MARK STEFFEL
 mark.steffel@gemarshall.com

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)