

OIL ANALYSIS REPORT

Area (TEMP) Preferred Service-Tractor [Preferred Service-Tractor]

Diesel Engine Fluic

PETRO CANADA DURON UHP 5W30 (36 QTS

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

Metal levels are typical for a new component breaking in.

Contamination

Elevated aluminum (Al) and/or lead (Pb) and potassium (K) levels in your metals analysis are likely a result of solder flux release into the lubricant and is common on new equipment/components. There is no indication of any contamination in the oil.

Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

] 192A320	37B					
TS)			Nov2023	Mar2024		
SAMPLE INFOR	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		PCA0120225	PCA0112167	
Sample Date		Client Info		28 Mar 2024	25 Nov 2023	
Machine Age	mls	Client Info		48760	24131	
Oil Age	mls	Client Info		24629	24128	
Oil Changed		Client Info		Not Changd	Changed	
Sample Status				NORMAL	ABNORMAL	
CONTAMINAT	ION	method	limit/base	current	history1	history2
Fuel		WC Method	>6.0	<1.0	<1.0	
Water		WC Method	>0.2	NEG	NEG	
Glycol		WC Method		NEG	NEG	
WEAR METAL	S	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>100	38	36	
Chromium	ppm	ASTM D5185m	>20	2	<1	
Nickel	ppm	ASTM D5185m	>2	4	<1	
Titanium	ppm	ASTM D5185m		<1	<1	
Silver	ppm	ASTM D5185m	>2	<1	0	
Aluminum	ppm	ASTM D5185m	>25	15	25	
Lead	ppm	ASTM D5185m	>40	<1	2	
Copper	ppm	ASTM D5185m	>330	267	261	
Tin	ppm	ASTM D5185m	>15	4	5	
Vanadium	ppm	ASTM D5185m		<1	<1	
Cadmium	ppm	ASTM D5185m		<1	0	
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	0	31	234	
Barium	ppm	ASTM D5185m	0	0	0	
Molybdenum	ppm	ASTM D5185m	64	87	118	
Manganese	ppm	ASTM D5185m	0	2	4	
Magnesium	ppm	ASTM D5185m	1160	1321	676	
Calcium	ppm	ASTM D5185m	820	1128	1497	
Phosphorus	ppm	ASTM D5185m	1160	1188	708	
Zinc	ppm	ASTM D5185m	1260	1553	808	
Sulfur	ppm	ASTM D5185m	3000	3614	2082	
CONTAMINAN	ITS	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	20	5 3	
Sodium	ppm	ASTM D5185m		6	7	
Potassium	ppm	ASTM D5185m	>20	44	64	
INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844	>3	0.6	0.5	
Nitration	Abs/cm	*ASTM D7624		10.6	10.3	
Sulfation	Abs/.1mm	*ASTM D7415	>30	23.0	25.1	
FLUID DEGRAI	DATION	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414	>25	21.2	23.6	
Base Number (BN)	mg KOH/g	ASTM D7414 ASTM D2896	>25	6.6	7.2	
	ing NOTing	A01W D2030	11.0	0.0	1.6	

Sample Rating Trend

NORMAL




Abnor


8


Nov25/23

OIL ANALYSIS REPORT

VISUAL







Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513 Sample No. : PCA0120225 Received : 05 Apr 2024 1955 W. North Avenue, Bldg K Lab Number : 06139521 : 05 Apr 2024 Melrose Park, IL Tested Unique Number : 10964329 Diagnosed : 05 Apr 2024 - Wes Davis US 60160 Test Package : FLEET Contact: Tom Lindeman Certificate 12367 To discuss this sample report, contact Customer Service at 1-800-237-1369. tlindemann@transervice.com * - Denotes test methods that are outside of the ISO 17025 scope of accreditation. T: (630)376-8946

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

E: