


OIL ANALYSIS REPORT



Area
East Chicago Operations
 Machine Id
LIEBHERR R912 MH-85 (S/N 5007455)
 Component
Rear Right Tandem
 Fluid
PETRO CANADA TRAXON 80W90 (--- GAL)

Sample Rating Trend



WEAR



DIAGNOSIS

▲ Recommendation

The oil change at the time of sampling has been noted. No corrective action is recommended at this time. Resample at the next service interval to monitor.

▲ Wear

The iron level is abnormal. All other metal levels are typical for a new component breaking in.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

SAMPLE INFORMATION

	method	limit/base	current	history1	history2
Sample Number	Client Info		PCA0113785	---	---
Sample Date	Client Info		28 Mar 2024	---	---
Machine Age	hrs	Client Info	1838	---	---
Oil Age	hrs	Client Info	1838	---	---
Oil Changed	Client Info		Changed	---	---
Sample Status			ABNORMAL	---	---

CONTAMINATION

	method	limit/base	current	history1	history2
Water	WC Method	>0.2	NEG	---	---

WEAR METALS

	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m >425	▲ 802	---	---
Chromium	ppm	ASTM D5185m >5	4	---	---
Nickel	ppm	ASTM D5185m >5	<1	---	---
Titanium	ppm	ASTM D5185m	0	---	---
Silver	ppm	ASTM D5185m	0	---	---
Aluminum	ppm	ASTM D5185m >5	3	---	---
Lead	ppm	ASTM D5185m	<1	---	---
Copper	ppm	ASTM D5185m >8	23	---	---
Tin	ppm	ASTM D5185m	<1	---	---
Vanadium	ppm	ASTM D5185m	0	---	---
Cadmium	ppm	ASTM D5185m	0	---	---

ADDITIVES

	method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m 243	118	---	---
Barium	ppm	ASTM D5185m 1	0	---	---
Molybdenum	ppm	ASTM D5185m	0	---	---
Manganese	ppm	ASTM D5185m	6	---	---
Magnesium	ppm	ASTM D5185m 2	4	---	---
Calcium	ppm	ASTM D5185m 6	32	---	---
Phosphorus	ppm	ASTM D5185m 987	1178	---	---
Zinc	ppm	ASTM D5185m 1	50	---	---
Sulfur	ppm	ASTM D5185m 21530	23496	---	---




CONTAMINANTS

	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m >50	18	---	---
Sodium	ppm	ASTM D5185m	14	---	---
Potassium	ppm	ASTM D5185m >20	2	---	---

FLUID DEGRADATION

	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045 1.9	1.54	---	---

OIL ANALYSIS REPORT











PARAMETER	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	---
Yellow Metal	scalar	*Visual	NONE	NONE	---
Precipitate	scalar	*Visual	NONE	NONE	---
Silt	scalar	*Visual	NONE	NONE	---
Debris	scalar	*Visual	NONE	NONE	---
Sand/Dirt	scalar	*Visual	NONE	NONE	---
Appearance	scalar	*Visual	NORML	NORML	---
Odor	scalar	*Visual	NORML	NORML	---
Emulsified Water	scalar	*Visual	>0.2	NEG	---
Free Water	scalar	*Visual		NEG	---

FLUID PROPERTIES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	141.0	139	---

SAMPLE IMAGES	method	limit/base	current	history1	history2
Color				no image	no image
Bottom				no image	no image

GRAPHS



Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : PCA0113785 **Received** : 05 Apr 2024
Lab Number : 06140083 **Tested** : 08 Apr 2024
Unique Number : 10964891 **Diagnosed** : 08 Apr 2024 - Don Baldrige
Test Package : MOB 2

SCRAP METAL SERVICES
 415 E 151ST STREET
 EAST CHICAGO, IN
 US 46312
 Contact: DAN GERTLER
 dgertler@scrapmetalservices.com
 T: (312)771-4999
 F:

To discuss this sample report, contact Customer Service at 1-800-237-1369.
 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)