


OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL



Machine Id
Truck 1
 Component
Gasoline Engine
 Fluid
 {not provided} (6 QTS)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

SAMPLE INFORMATION		method	limit/base	current	history1	history2
Sample Number	Client Info			PCA0104504	PCA0023192	---
Sample Date	Client Info			04 Mar 2024	25 Sep 2020	---
Machine Age	mls	Client Info		170002	102863	---
Oil Age	mls	Client Info		5000	7000	---
Oil Changed	Client Info			Changed	Changed	---
Sample Status				NORMAL	NORMAL	---

CONTAMINATION		method	limit/base	current	history1	history2
Water	WC Method	>0.2		NEG	NEG	---
Glycol	WC Method			NEG	NEG	---

WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>150	13	16	---
Chromium	ppm	ASTM D5185m	>20	<1	1	---
Nickel	ppm	ASTM D5185m	>5	0	<1	---
Titanium	ppm	ASTM D5185m		<1	24	---
Silver	ppm	ASTM D5185m	>2	0	0	---
Aluminum	ppm	ASTM D5185m	>40	3	0	---
Lead	ppm	ASTM D5185m	>50	0	0	---
Copper	ppm	ASTM D5185m	>155	7	16	---
Tin	ppm	ASTM D5185m	>10	<1	<1	---
Antimony	ppm	ASTM D5185m		---	0	---
Vanadium	ppm	ASTM D5185m		0	<1	---
Cadmium	ppm	ASTM D5185m		0	0	---




ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		37	46	---
Barium	ppm	ASTM D5185m		0	<1	---
Molybdenum	ppm	ASTM D5185m		65	112	---
Manganese	ppm	ASTM D5185m		<1	2	---
Magnesium	ppm	ASTM D5185m		505	672	---
Calcium	ppm	ASTM D5185m		1117	1125	---
Phosphorus	ppm	ASTM D5185m		689	625	---
Zinc	ppm	ASTM D5185m		757	746	---
Sulfur	ppm	ASTM D5185m		3155	1883	---

CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>30	12	19	---
Sodium	ppm	ASTM D5185m	>400	4	24	---
Potassium	ppm	ASTM D5185m	>20	<1	<1	---
Fuel	%	ASTM D3524	>4.0	<1.0	<1.0	---

INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844		0.1	0	---
Nitration	Abs/cm	*ASTM D7624	>20	11.5	11.8	---
Sulfation	Abs/.1mm	*ASTM D7415	>30	25.4	25.1	---

FLUID DEGRADATION		method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414	>25	20.9	19	---
Acid Number (AN)	mg KOH/g	ASTM D8045		2.19	2.126	---









OIL ANALYSIS REPORT



VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	---
Yellow Metal	scalar	*Visual	NONE	NONE	---
Precipitate	scalar	*Visual	NONE	NONE	---
Silt	scalar	*Visual	NONE	NONE	---
Debris	scalar	*Visual	NONE	NONE	---
Sand/Dirt	scalar	*Visual	NONE	NONE	---
Appearance	scalar	*Visual	NORML	NORML	---
Odor	scalar	*Visual	NORML	NORML	---
Emulsified Water	scalar	*Visual	>0.2	NEG	---
Free Water	scalar	*Visual		NEG	---

FLUID PROPERTIES	method	limit/base	current	history1	history2
Visc @ 100°C	cSt	ASTM D445	7.6	8.0	---

GRAPHS



Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : PCA0104504 **Received** : 05 Apr 2024
Lab Number : **06140687** **Tested** : 10 Apr 2024
Unique Number : 10965495 **Diagnosed** : 10 Apr 2024 - Jonathan Hester
Test Package : MOB 2 (Additional Tests: FuelDilution, PercentFuel)

J F PRICE
 611 PLEASANT ST
 E WEYMOUTH, MA
 US 02189
 Contact: JOHN LANG
 gnalj1970@comcast.net
 T: (617)435-7199
 F: (781)337-4150

To discuss this sample report, contact Customer Service at 1-800-237-1369.
 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)