


OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL



Machine Id
FREIGHTLINER 698047
 Component
Diesel Engine
 Fluid
PETRO CANADA DURON SHP 10W30 (36 QTS)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

SAMPLE INFORMATION

	method	limit/base	current	history1	history2
Sample Number	Client Info		PCA0119403	PCA0071684	PCA0053345
Sample Date	Client Info		28 Feb 2024	12 Sep 2022	24 Oct 2021
Machine Age	mls	Client Info	309012	207312	142585
Oil Age	mls	Client Info	64330	64727	43314
Oil Changed	Client Info		Changed	Changed	Changed
Sample Status			NORMAL	NORMAL	NORMAL

CONTAMINATION

	method	limit/base	current	history1	history2
Fuel	WC Method	>3.0	<1.0	<1.0	<1.0
Water	WC Method	>0.2	NEG	NEG	NEG
Glycol	WC Method		NEG	NEG	NEG

WEAR METALS

	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m >65	49	54	31
Chromium	ppm	ASTM D5185m >5	2	4	3
Nickel	ppm	ASTM D5185m >3	0	1	<1
Titanium	ppm	ASTM D5185m >5	11	4	<1
Silver	ppm	ASTM D5185m >2	0	1	0
Aluminum	ppm	ASTM D5185m >35	18	27	18
Lead	ppm	ASTM D5185m >10	0	1	0
Copper	ppm	ASTM D5185m >180	15	26	27
Tin	ppm	ASTM D5185m >8	1	3	1
Antimony	ppm	ASTM D5185m >35	---	---	1
Vanadium	ppm	ASTM D5185m	0	2	0
Cadmium	ppm	ASTM D5185m	0	<1	0

ADDITIVES

	method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m 2	7	2	13
Barium	ppm	ASTM D5185m 0	0	<1	0
Molybdenum	ppm	ASTM D5185m 50	56	58	44
Manganese	ppm	ASTM D5185m 0	<1	2	<1
Magnesium	ppm	ASTM D5185m 950	949	878	602
Calcium	ppm	ASTM D5185m 1050	1304	1323	1775
Phosphorus	ppm	ASTM D5185m 995	1083	978	703
Zinc	ppm	ASTM D5185m 1180	1300	1216	899
Sulfur	ppm	ASTM D5185m 2600	3150	2564	2554

CONTAMINANTS

	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m >15	8	8	8
Sodium	ppm	ASTM D5185m	6	6	5
Potassium	ppm	ASTM D5185m >20	11	25	30




INFRA-RED

	method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844 >3	2.3	2.9	1.5
Nitration	Abs/cm	*ASTM D7624 >20	13.7	16.2	12.8
Sulfation	Abs/.1mm	*ASTM D7415 >30	28.4	32.9	26.1

FLUID DEGRADATION

	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414 >25	22.9	27.4	25.2
Base Number (BN)	mg KOH/g	ASTM D2896	4.5	5.1	---









OIL ANALYSIS REPORT



PARAMETER	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG

FLUID PROPERTIES	method	limit/base	current	history1	history2
Visc @ 100°C	cSt	ASTM D445	12.00	12.4	12.1

GRAPHS



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : PCA0119403
Lab Number : 06140806
Unique Number : 10965614
Test Package : MOB 1 (Additional Tests: TBN)

Received : 08 Apr 2024
Tested : 08 Apr 2024
Diagnosed : 08 Apr 2024 - Wes Davis

MILLER TRUCK LEASING #123
 66 KELLER AVENUE
 LANCASTER, PA
 US 17601
 Contact: RON ROBERTS
 roberts@millertransgroup.com
 T: (717)945-6205
 F: (717)945-5818

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)