




OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL



Machine Id
413003
 Component
Diesel Engine
 Fluid
PETRO CANADA DURON SHP 15W40 (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

SAMPLE INFORMATION		method	limit/base	current	history1	history2
Sample Number	Client Info			GFL0104482	GFL0104442	GFL0104297
Sample Date	Client Info			03 Apr 2024	02 Apr 2024	07 Mar 2024
Machine Age	hrs	Client Info		1579	1579	1435
Oil Age	hrs	Client Info		600	600	600
Oil Changed	Client Info			Changed	Changed	N/A
Sample Status				NORMAL	---	NORMAL

CONTAMINATION		method	limit/base	current	history1	history2
Fuel	WC Method	>3.0		<1.0	<1.0	<1.0
Water	WC Method	>0.2		NEG	NEG	NEG
Glycol	WC Method			NEG	NEG	NEG

WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>120	5	---	8
Chromium	ppm	ASTM D5185m	>20	<1	---	0
Nickel	ppm	ASTM D5185m	>5	<1	---	0
Titanium	ppm	ASTM D5185m	>2	<1	---	0
Silver	ppm	ASTM D5185m	>2	<1	---	0
Aluminum	ppm	ASTM D5185m	>20	3	---	1
Lead	ppm	ASTM D5185m	>40	<1	---	0
Copper	ppm	ASTM D5185m	>330	3	---	16
Tin	ppm	ASTM D5185m	>15	<1	---	0
Vanadium	ppm	ASTM D5185m		<1	---	0
Cadmium	ppm	ASTM D5185m		<1	---	0

ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	0	2	---	8
Barium	ppm	ASTM D5185m	0	0	---	0
Molybdenum	ppm	ASTM D5185m	60	62	---	61
Manganese	ppm	ASTM D5185m	0	<1	---	0
Magnesium	ppm	ASTM D5185m	1010	967	---	829
Calcium	ppm	ASTM D5185m	1070	1079	---	962
Phosphorus	ppm	ASTM D5185m	1150	981	---	788
Zinc	ppm	ASTM D5185m	1270	1235	---	1017
Sulfur	ppm	ASTM D5185m	2060	3139	---	2593




CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	6	---	9
Sodium	ppm	ASTM D5185m		2	---	2
Potassium	ppm	ASTM D5185m	>20	3	---	4

INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844	>4	0.1	---	0.2
Nitration	Abs/cm	*ASTM D7624	>20	5.5	---	6.7
Sulfation	Abs/.1mm	*ASTM D7415	>30	18.0	---	19.0

FLUID DEGRADATION		method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414	>25	14.2	---	15.3
Base Number (BN)	mg KOH/g	ASTM D2896	9.8	8.9	---	7.8







OIL ANALYSIS REPORT



PARAMETER	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG

FLUID PROPERTIES	method	limit/base	current	history1	history2	
Visc @ 100°C	cSt	ASTM D445	15.4	14.0	14.0	13.1

GRAPHS



Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : GFL0104482 **Received** : 08 Apr 2024
Lab Number : **06140952** **Tested** : 08 Apr 2024
Unique Number : 10965760 **Diagnosed** : 08 Apr 2024 - Wes Davis
Test Package : FLEET

GFL Environmental - 410 - Michigan West
 39000 Van Born Rd
 Wayne, MI
 US 48184

To discuss this sample report, contact Customer Service at 1-800-237-1369.
 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)