

OIL ANALYSIS REPORT

Sample Rating Trend



Machine Id

11319 Component

Component Transmission (Auto) Fluid

PETRO CANADA DuraDrive HD Synthetic 668 (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor. Please specify the component make and model with your next sample.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the fluid.


Fluid Condition

The condition of the fluid is acceptable for the time in service.


SAMPLE INFOR	MATION	method	limit/base	current	history1	history2	
Sample Number		Client Info		GFL0115696	GFL0115749	GFL0107182	
Sample Date		Client Info		05 Apr 2024	11 Mar 2024	30 Jan 2024	
Machine Age	hrs	Client Info		7689	7551	7313	
Oil Age	hrs	Client Info		138	918	680	
Oil Changed		Client Info		Not Changd	Changed	Not Changd	
Sample Status				NORMAL	NORMAL	NORMAL	
CONTAMINAT	ION	method	limit/base	current	history1	history2	
Water		WC Method	>0.1	NEG	NEG	NEG	
WEAR METAL	S	method	limit/base	current	history1	history2	
Iron	ppm	ASTM D5185m	>160	46	52	52	
Chromium	ppm	ASTM D5185m	>5	<1	0	<1	
Nickel	ppm	ASTM D5185m	>5	0	0	<1	
Titanium	ppm	ASTM D5185m		<1	0	<1	
Silver	ppm	ASTM D5185m	>5	0	0	0	
Aluminum	ppm	ASTM D5185m	>50	13	13	11	
Lead	ppm	ASTM D5185m	>50	2	1	4	
Copper	ppm	ASTM D5185m	>225	18	18	19	
Tin	ppm	ASTM D5185m	>10	2	1	3	
Vanadium	ppm	ASTM D5185m		<1	0	0	
Cadmium	ppm	ASTM D5185m		0	0	<1	
ADDITIVES		method	limit/base	current	history1	history2	
Boron	ppm	ASTM D5185m		69	61	67	
Barium	ppm	ASTM D5185m		0	0	0	
Molybdenum	ppm	ASTM D5185m		<1	0	<1	
Manganese	ppm	ASTM D5185m		<1	<1	1	
Magnesium	ppm	ASTM D5185m		3	0	2	
Calcium	ppm	ASTM D5185m		132	108	109	
Phosphorus	ppm	ASTM D5185m		267	227	240	
Zinc	ppm	ASTM D5185m		9	0	0	
Sulfur	ppm	ASTM D5185m		1874	1690	1569	
CONTAMINAN	ITS	method	limit/base	current	history1	history2	
Silicon	ppm	ASTM D5185m	>20	5	4	5	
Sodium	ppm	ASTM D5185m		6	7	2	
Potassium	ppm	ASTM D5185m	>20	4	2	3	
VISUAL		method	limit/base	current	history1	history2	
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE	
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE	
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE	
Silt	scalar	*Visual	NONE	NONE	NONE	NONE	
Debris	scalar	*Visual	NONE	NONE	NONE	NONE	
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE	
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML	
Odor	scalar	*Visual	NORML	NORML	NORML	NORML	
Emulsified Water	scalar	*Visual	>0.1	NEG	NEG	NEG	
Free Water 3:33:58) Rev: 1	scalar	*Visual		NEG	NEG Submitted By: JC		
.33.30) Nev. 1	Rev: 1 Submitted By: JOSHUA TINKE						



OIL ANALYSIS REPORT



Visc @ 40°C	cSt	ASTM D445	34	33.1	33.2	33.4
SAMPLE IM	AGES	method	limit/base	current	history1	hist
Color				no image	no image	no im
Bottom				no image	no image	no im
GRAPHS						
Ferrous Alloys						
50 - iron iron chromium	/ ~	$\overline{\mathbf{n}}$				
40 -		V				
30 -						
20-						
10						
Jan20/23	Jun22/23 Sep 1/23	0ct30/23 Jan30/24	Apr5/24			
Non-ferrous Me		Ja D	4			
copper	~/		_			
16tin 14 -	/~	V				
12-						
8-						
4		40				
Jan20/23	Jun22/23	0ct30/23	Apr5/24			
^{سهر} الع Viscosity @ 40°		0ct Jan	A			
39 38 Abnormal						
37-						
35 - Base						
32 - 31 - Abnomal						
30 Abnormal		3	4			
Jan 20/23 Mar 16/23 Apr 25/23	Jun22/23 . Sep1/23 .	0ct30/23 Jan30/24	Apr5/24			



Submitted By: JOSHUA TINKER Page 2 of 2