


OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL



Area
(51472Z) Walgreens - Tractor
 Machine Id
[Walgreens - Tractor] 136A63327
 Component
Diesel Engine
 Fluid
PETRO CANADA DURON SHP 10W30 (11 GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

SAMPLE INFORMATION

method	limit/base	current	history1	history2
Sample Number	Client Info	PCA0106573	PCA0094985	PCA0094903
Sample Date	Client Info	03 Apr 2024	15 Sep 2023	06 Jun 2023
Machine Age	mls Client Info	272614	211650	154006
Oil Age	mls Client Info	60000	60000	40000
Oil Changed	Client Info	Filtered	Changed	Changed
Sample Status		NORMAL	NORMAL	NORMAL

CONTAMINATION

method	limit/base	current	history1	history2
Fuel	WC Method >5	<1.0	<1.0	<1.0
Water	WC Method >0.2	NEG	NEG	NEG
Glycol	WC Method	NEG	NEG	NEG

WEAR METALS

method	limit/base	current	history1	history2
Iron	ppm ASTM D5185m >80	30	46	34
Chromium	ppm ASTM D5185m >5	3	4	4
Nickel	ppm ASTM D5185m >2	<1	0	<1
Titanium	ppm ASTM D5185m	<1	0	<1
Silver	ppm ASTM D5185m >3	0	0	0
Aluminum	ppm ASTM D5185m >30	10	29	31
Lead	ppm ASTM D5185m >30	0	0	0
Copper	ppm ASTM D5185m >150	23	5	51
Tin	ppm ASTM D5185m >5	0	0	<1
Vanadium	ppm ASTM D5185m	<1	0	<1
Cadmium	ppm ASTM D5185m	0	0	<1

ADDITIVES

method	limit/base	current	history1	history2
Boron	ppm ASTM D5185m 2	7	<1	0
Barium	ppm ASTM D5185m 0	0	0	0
Molybdenum	ppm ASTM D5185m 50	59	61	63
Manganese	ppm ASTM D5185m 0	<1	<1	1
Magnesium	ppm ASTM D5185m 950	997	1048	1077
Calcium	ppm ASTM D5185m 1050	1172	1156	1258
Phosphorus	ppm ASTM D5185m 995	978	1058	989
Zinc	ppm ASTM D5185m 1180	1232	1338	1286
Sulfur	ppm ASTM D5185m 2600	2890	2948	2480

CONTAMINANTS

method	limit/base	current	history1	history2
Silicon	ppm ASTM D5185m >20	6	6	6
Sodium	ppm ASTM D5185m	2	2	3
Potassium	ppm ASTM D5185m >20	17	25	64




INFRA-RED

method	limit/base	current	history1	history2
Soot %	% *ASTM D7844 >3	0.6	1.2	0.6
Nitration	Abs/cm *ASTM D7624 >20	9.4	10.8	10.4
Sulfation	Abs/.1mm *ASTM D7415 >30	21.7	24.5	22.8

FLUID DEGRADATION

method	limit/base	current	history1	history2
Oxidation	Abs/.1mm *ASTM D7414 >25	19.1	21.0	22.4
Base Number (BN)	mg KOH/g ASTM D2896	5.6	4.5	4.6





OIL ANALYSIS REPORT



PARAMETER	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG

FLUID PROPERTIES	method	limit/base	current	history1	history2
Visc @ 100°C	cSt	ASTM D445	12.00	11.6	12.3

GRAPHS



Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : PCA0106573
Lab Number : 06142005
Unique Number : 10966813
Test Package : FLEET

Transervice - Shop 1369 - Berkeley-Waxahachie
 710 Ovilla Road
 Waxahachie, TX
 US 75167

To discuss this sample report, contact Customer Service at 1-800-237-1369.
 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)