

OIL ANALYSIS REPORT

Sample Rating Trend

NORMAL

Machine Id

725047-310032

Component Transmission (Auto)

Fluid PETRO CANADA DuraDrive HD Synthetic 668 (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the fluid.


Fluid Condition

The condition of the fluid is acceptable for the time in service.

SAMPLE INFORM	1ATION	method	limit/base	current	history1	history2
Sample Number		Client Info		GFL0114057	GFL0095138	GFL0070328
Sample Date		Client Info		09 Apr 2024	16 Oct 2023	25 Apr 2023
Machine Age	hrs	Client Info		18887	0	17022
Oil Age	hrs	Client Info		0	0	600
Oil Changed		Client Info		Not Changd	N/A	Changed
Sample Status				NORMAL	NORMAL	NORMAL
CONTAMINATI	ON	method	limit/base	current	history1	history2
Water		WC Method	>0.1	NEG	NEG	NEG
WEAR METALS	6	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>160	42	60	171
Chromium	ppm	ASTM D5185m	>5	0	<1	<1
Nickel	ppm	ASTM D5185m	>5	0	<1	0
Titanium	ppm	ASTM D5185m		0	0	<1
Silver	ppm	ASTM D5185m	>5	0	0	<1
Aluminum	ppm	ASTM D5185m	>50	4	35	27
Lead	ppm	ASTM D5185m	>50	0	24	0
Copper	ppm	ASTM D5185m	>225	2	12	18
Tin	ppm	ASTM D5185m	>10	0	8	1
Vanadium	ppm	ASTM D5185m		0	0	0
Cadmium	ppm	ASTM D5185m		0	0	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		78	88	87
Barium	ppm	ASTM D5185m		0	0	0
Molybdenum	ppm	ASTM D5185m		1	0	<1
Manganese	ppm	ASTM D5185m		0	2	3
Magnesium	ppm	ASTM D5185m		49	0	13
Calcium	ppm	ASTM D5185m		173	73	114
Phosphorus	ppm	ASTM D5185m		257	277	233
Zinc	ppm	ASTM D5185m		46	0	21
Sulfur	ppm	ASTM D5185m		1942	1310	1692
CONTAMINAN	ſS	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>20	6	5	12
Sodium	ppm	ASTM D5185m		4	9	10
Potassium	ppm	ASTM D5185m	>20	1	6	1
VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	LIGHT
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.1	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG
:43:26) Rev: 1			cation: GFL8		7,840 - Loyce St	



OIL ANALYSIS REPORT



FLUID PROPERTIES method Visc @ 40°C ASTM D445 34 33.13 34.7 34.04 cSt SAMPLE IMAGES Color no image no image no image Bottom no image no image no image GRAPHS Ferrous Alloys 180 160 140 nicke 120 100 80 60 40 20 n Apr21/22 .pr25/23 Oct16/23 -eb27/23 kpr9/24 Non-ferrous Metals 2! 20 15 10 0 pr25/23 eb27/23 Apr21 Viscosity @ 40°C 39 38 37 36 () 35 0€ 34 ŝ 33 32 31 30 29 Apr9/24 -Oct16/23 Apr21/22 eb27/23 Apr25/23 Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513 GFL Environmental - 836 - Kansas City Hauling Sample No. : GFL0114057 Received 7801 East Truman Road : 12 Apr 2024 Lab Number : 06146988 Tested : 18 Apr 2024 Kansas City, MO Diagnosed : 18 Apr 2024 - Jonathan Hester



 Unique Number
 : 10977066
 Diagnosed
 : 18 Apr 2024 - Jonathan Hester

 Certificate L2367
 Test Package
 : FLEET (Additional Tests: KV100)
 Ioy

 To discuss this sample report, contact Customer Service at 1-800-237-1369.
 Ioy
 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

GFL Environmental - 830 - Kansas City Hauling 7801 East Truman Road Kansas City, MO US 64126 Contact: Loyce Stewart loyce.stewart@gflenv.com T: *GM 106:2012)* F:

Contact/Location: GFL823,834,836,837,840 - Loyce Stewart - GFL836