

OIL ANALYSIS REPORT



Machine Id 2327139 Component Diesel Engine Fluid PETRO CANADA DURON SHP 10W30 (--- 0

DIAGNOSIS

Recommendation

No corrective action is recommended at this time. Resample at the next service interval to monitor.

Wear

Metal levels are typical for a new component breaking in.

Contamination

Elevated aluminum (Al) and/or lead (Pb) and potassium (K) levels in your metals analysis are likely a result of solder flux release into the lubricant and is common on new equipment/components. There is no indication of any contamination in the oil.


Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is acceptable for the time in service.

rs)				Apr2024		
SAMPLE INFORM	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		PCA0122272		
Sample Date		Client Info		02 Apr 2024		
Machine Age	mls	Client Info		47374		
Dil Age	mls	Client Info		0		
Dil Changed		Client Info		N/A		
Sample Status				NORMAL		
CONTAMINAT	ION	method	limit/base	current	history1	history2
uel		WC Method	>5	<1.0		
Vater		WC Method	>0.2	NEG		
Glycol		WC Method		NEG		
WEAR METAL	S	method	limit/base	current	history1	history2
ron	ppm	ASTM D5185m	>100	83		
Chromium	ppm	ASTM D5185m	>20	1		
Nickel	ppm	ASTM D5185m	>4	0		
Fitanium	ppm	ASTM D5185m		0		
Silver	ppm	ASTM D5185m	>3	0		
Aluminum	ppm	ASTM D5185m	>20	41		
ead	ppm	ASTM D5185m	>40	<1		
Copper	ppm	ASTM D5185m	>330	261		
Γin	ppm	ASTM D5185m	>15	6		
/anadium	ppm	ASTM D5185m		0		
Cadmium	ppm	ASTM D5185m		0		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	2	29		
Barium	ppm	ASTM D5185m	0	<1		
Nolybdenum	ppm	ASTM D5185m	50	115		
Manganese	ppm	ASTM D5185m	0	5		
Magnesium	ppm	ASTM D5185m	950	740		
Calcium	ppm	ASTM D5185m	1050	1463		
Phosphorus	ppm	ASTM D5185m	995	759		
Zinc	ppm	ASTM D5185m	1180	903		
Sulfur	ppm	ASTM D5185m	2600	2442		
CONTAMINAN	TS	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	65		
Sodium	ppm	ASTM D5185m		6		
Potassium	ppm	ASTM D5185m	>20	114		
INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844	>3	0.9		
Vitration	Abs/cm	*ASTM D7624	>20	13.5		
ination			>30	25.6		
Sulfation	Abs/.1mm	*ASTM D7415	200	23.0		
			limit/base	current	history1	history2
Sulfation						history2



OIL ANALYSIS REPORT



Contact/Location: JOHNNY LASSITER - PERCOF