# PROBLEM SUMMARY

Machine Id
**723031-303001**
Component
**Diesel Engine**
Fluid
**PETRO CANADA DURON SHP 15W40 (--- GAL)**

**Sample Rating Trend**



**FUEL**

## COMPONENT CONDITION SUMMARY







## RECOMMENDATION

We advise that you check the fuel injection system. We recommend that you drain the oil from the component if this has not already been done. We recommend an early resample to monitor this condition.

## PROBLEMATIC TEST RESULTS

| Sample Status | | | | SEVERE | NORMAL | ABNORMAL |
|---|---|---|---|---|---|---|
| Fuel | % | ASTM D3524 | >5 | ▲ **12.2** | <1.0 | <1.0 |
| Visc @ 100°C | cSt | ASTM D445 | 15.4 | ▲ **11.3** | 14.2 | 12.9 |

**Customer Id:** GFL837
**Sample No.:** GFL0114192
**Lab Number:** 06149330
**Test Package:** FLEET

*To manage this report scan the QR code*

*To discuss the diagnosis or test data:*
Wes Davis +1 905-569-8600 x223
wesd@wearcheck.ca

*To change component or sample information:*
Customer Service +1 1-800-237-1369
customerservice@wearcheck.com

## RECOMMENDED ACTIONS

| Action | Status | Date | Done By | Description |
|---|---|---|---|---|
| Change Fluid | --- | --- | ? | We recommend that you drain the oil from the component if this has not already been done. |
| Resample | --- | --- | ? | We recommend an early resample to monitor this condition. |
| Check Fuel/injector System | --- | --- | ? | We advise that you check the fuel injection system. |

## HISTORICAL DIAGNOSIS

NORMAL

**05 Mar 2024 Diag: Wes Davis**
Resample at the next service interval to monitor.All component wear rates are normal. There is no indication of any contamination in the oil. The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

view report

SOOT

**31 Jan 2024 Diag: Jonathan Hester**
We recommend you service the filters on this component. Resample at the next service interval to monitor.All component wear rates are normal. There is an abnormal amount of solids and carbon present in the oil. The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

view report

NORMAL

**06 Jan 2024 Diag: Wes Davis**
Resample at the next service interval to monitor.All component wear rates are normal. There is no indication of any contamination in the oil. The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

view report

# OIL ANALYSIS REPORT

Machine Id
**723031-303001**
Component
**Diesel Engine**
Fluid
**PETRO CANADA DURON SHP 15W40 (--- GAL)**

Sample Rating Trend



**FUEL**

## DIAGNOSIS

**Recommendation**
We advise that you check the fuel injection system. We recommend that you drain the oil from the component if this has not already been done. We recommend an early resample to monitor this condition.

**Wear**
All component wear rates are normal.

**Contamination**
There is a high amount of fuel present in the oil. Tests confirm the presence of fuel in the oil.

**Fluid Condition**
The BN result indicates that there is suitable alkalinity remaining in the oil. Fuel is present in the oil and is lowering the viscosity. The oil is no longer serviceable due to the presence of contaminants.

| SAMPLE INFORMATION | | method | limit/base | current | history1 | history2 |
|---|---|---|---|---|---|---|
| Sample Number | | Client Info | | **GFL0114192** | GFL0114123 | GFL0108109 |
| Sample Date | | Client Info | | **02 Apr 2024** | 05 Mar 2024 | 31 Jan 2024 |
| Machine Age | hrs | Client Info | | **25599** | 20451 | 20305 |
| Oil Age | hrs | Client Info | | **5408** | 19807 | 0 |
| Oil Changed | | Client Info | | **Not Changd** | Changed | Not Changd |
| Sample Status | | | | **SEVERE** | NORMAL | ABNORMAL |

| CONTAMINATION | | method | limit/base | current | history1 | history2 |
|---|---|---|---|---|---|---|
| Water | | WC Method | >0.2 | **NEG** | NEG | NEG |
| Glycol | | WC Method | | **NEG** | NEG | NEG |

| WEAR METALS | | method | limit/base | current | history1 | history2 |
|---|---|---|---|---|---|---|
| Iron | ppm | ASTM D5185m | >80 | **33** | 51 | 53 |
| Chromium | ppm | ASTM D5185m | >5 | **1** | 2 | 2 |
| Nickel | ppm | ASTM D5185m | >2 | **0** | <1 | 0 |
| Titanium | ppm | ASTM D5185m | | **0** | 0 | 0 |
| Silver | ppm | ASTM D5185m | >3 | **0** | 0 | 0 |
| Aluminum | ppm | ASTM D5185m | >30 | **5** | 5 | 6 |
| Lead | ppm | ASTM D5185m | >30 | **0** | <1 | 0 |
| Copper | ppm | ASTM D5185m | >150 | **<1** | 1 | 1 |
| Tin | ppm | ASTM D5185m | >5 | **<1** | 0 | <1 |
| Vanadium | ppm | ASTM D5185m | | **0** | <1 | 0 |
| Cadmium | ppm | ASTM D5185m | | **0** | 0 | 0 |

| ADDITIVES | | method | limit/base | current | history1 | history2 |
|---|---|---|---|---|---|---|
| Boron | ppm | ASTM D5185m | 0 | **3** | 1 | 4 |
| Barium | ppm | ASTM D5185m | 0 | **0** | 0 | 0 |
| Molybdenum | ppm | ASTM D5185m | 60 | **57** | 59 | 54 |
| Manganese | ppm | ASTM D5185m | 0 | **<1** | <1 | <1 |
| Magnesium | ppm | ASTM D5185m | 1010 | **926** | 1007 | 834 |
| Calcium | ppm | ASTM D5185m | 1070 | **1051** | 1136 | 893 |
| Phosphorus | ppm | ASTM D5185m | 1150 | **1043** | 1049 | 924 |
| Zinc | ppm | ASTM D5185m | 1270 | **1216** | 1293 | 1138 |
| Sulfur | ppm | ASTM D5185m | 2060 | **3217** | 3366 | 2360 |

| CONTAMINANTS | | method | limit/base | current | history1 | history2 |
|---|---|---|---|---|---|---|
| Silicon | ppm | ASTM D5185m | >20 | **17** | 10 | 7 |
| Sodium | ppm | ASTM D5185m | | **6** | 6 | 6 |
| Potassium | ppm | ASTM D5185m | >20 | **2** | <1 | 0 |
| Fuel | % | ASTM D3524 | >5 | ▲ **12.2** | <1.0 | <1.0 |

| INFRA-RED | | method | limit/base | current | history1 | history2 |
|---|---|---|---|---|---|---|
| Soot % | % | *ASTM D7844 | >3 | **0.9** | 1.9 | ▲ 3 |
| Nitration | Abs/cm | *ASTM D7624 | >20 | **9.6** | 12.2 | 16.1 |
| Sulfation | Abs/.1mm | *ASTM D7415 | >30 | **20.6** | 23.9 | 29.1 |

| FLUID DEGRADATION | | method | limit/base | current | history1 | history2 |
|---|---|---|---|---|---|---|
| Oxidation | Abs/.1mm | *ASTM D7414 | >25 | **17.6** | 21.1 | 27.8 |
| Base Number (BN) | mg KOH/g | ASTM D2896 | 9.8 | **8.7** | 9.1 | 5.6 |

# OIL ANALYSIS REPORT

Fuel Dilution




FT-IR (Direct Trend)




FT-IR (Direct Trend)




Base Number




| VISUAL | | method | limit/base | current | history1 | history2 |
|---|---|---|---|---|---|---|
| White Metal | scalar | *Visual | NONE | **NONE** | NONE | NONE |
| Yellow Metal | scalar | *Visual | NONE | **NONE** | NONE | NONE |
| Precipitate | scalar | *Visual | NONE | **NONE** | NONE | NONE |
| Silt | scalar | *Visual | NONE | **NONE** | NONE | NONE |
| Debris | scalar | *Visual | NONE | **NONE** | NONE | NONE |
| Sand/Dirt | scalar | *Visual | NONE | **NONE** | NONE | NONE |
| Appearance | scalar | *Visual | NORML | **NORML** | NORML | NORML |
| Odor | scalar | *Visual | NORML | **NORML** | NORML | NORML |
| Emulsified Water | scalar | *Visual | >0.2 | **NEG** | NEG | NEG |
| Free Water | scalar | *Visual | | **NEG** | NEG | NEG |

| FLUID PROPERTIES | | method | limit/base | current | history1 | history2 |
|---|---|---|---|---|---|---|
| Visc @ 100°C | cSt | ASTM D445 | 15.4 | ▲ **11.3** | 14.2 | 12.9 |

## GRAPHS

Ferrous Alloys




Non-ferrous Metals




Viscosity @ 100°C




Base Number




Certificate L2367

**Laboratory** : WearCheck USA - 501 Madison Ave., Cary, NC 27513
**Sample No.** : GFL0114192 **Received** : 15 Apr 2024
**Lab Number** : 06149330 **Tested** : 19 Apr 2024
**Unique Number** : 10979408 **Diagnosed** : 19 Apr 2024 - Wes Davis
**Test Package** : FLEET ( Additional Tests: FuelDilution, PercentFuel )

*To discuss this sample report, contact Customer Service at 1-800-237-1369.*
** - Denotes test methods that are outside of the ISO 17025 scope of accreditation.*
*Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)*

**GFL Environmental - 837 - Harrison TS**
22820 S State Route 291
Harrisonville, MO
US 64701
Contact: SARA PATRICK
spatrick@gflenv.com
T:
F:

Report Id: GFL837 [WUSCAR] 06149330 (Generated: 04/19/2024 08:55:55) Rev: 1

Submitted By: JEREMY BROWN