


# **OIL ANALYSIS REPORT**



 $\checkmark$ 

NORMAL



(62A1037) ALEXANDER CITY 413057 Diesel Engine

Ares

PETRO CANADA DURON SHP 15W40 (--- GAL)

#### SAMPLE INFORMATION method GFL0079742 GFL0089934 GFL0089931 Sample Number **Client Info** Sample Date Client Info 10 Apr 2024 02 Apr 2024 26 Mar 2024 2460 Machine Age hrs **Client Info** 2397 2363 Oil Age hrs Client Info 0 2397 2363 Oil Changed Client Info N/A N/A N/A NORMAL Sample Status NORMAL NORMAL CONTAMINATION Fuel >3.0 <1.0 WC Method <1.0 <1.0 Water WC Method >0.2 NEG NEG NEG Glycol WC Method NEG NEG NEG WEAR METALS >120 7 9 Iron 9 ppm ASTM D5185m ASTM D5185m >20 0 0 Chromium ppm <1 0 Nickel >5 <1 ppm ASTM D5185m <1 Titanium ppm ASTM D5185m >2 0 0 0 Silver ASTM D5185m >2 0 0 0 ppm 3 2 Aluminum ASTM D5185m >20 2 ppm 0 0 Lead ASTM D5185m >40 0 ppm ASTM D5185m >330 2 Copper ppm <1 1 0 Tin ppm ASTM D5185m >15 <1 <1 Vanadium ppm ASTM D5185m 0 0 0 Cadmium 0 0 0 ASTM D5185m ppm ADDITIVES Boron mag ASTM D5185m 0 8 10 8 Barium ASTM D5185m 0 0 0 0 ppm 59 Molybdenum ASTM D5185m 60 62 62 ppm ASTM D5185m 0 0 Manganese ppm 0 <1 Magnesium ASTM D5185m 1010 867 851 967 ppm Calcium ppm ASTM D5185m 1070 1125 1025 1150 Phosphorus ASTM D5185m 1150 1070 917 1042 ppm Zinc ppm ASTM D5185m 1270 1210 1105 1267 Sulfur ASTM D5185m 2060 2894 2960 3762 ppm CONTAMINANTS 6 5 4 Silicon ASTM D5185m >25 ppm 2 Sodium ASTM D5185m 2 2 ppm Potassium ASTM D5185m >20 5 2 ppm <1 **INFRA-RED** 0.3 % 0.3 0.3 Soot % \*ASTM D7844 >4 Nitration Abs/cm \*ASTM D7624 >20 7.7 7.5 7.4 Sulfation \*ASTM D7415 >30 18.5 18.4 18.2 Abs/.1mm FLUID DEGRADATION \*ASTM D7414 >25 14.3 14.1 14.1 Oxidation Abs/.1mm

Base Number (BN) mg KOH/g ASTM D2896 9.8

DIAGNOSIS

### Recommendation

Resample at the next service interval to monitor.

### Wear

All component wear rates are normal.

### Contamination

There is no indication of any contamination in the oil.

#### Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

7.2


7.1

7.0




## **OIL ANALYSIS REPORT**






VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG
FLUID PROPE	RTIES	method	limit/base	current	history1	history2
Visc @ 100°C	cSt	ASTM D445	15.4	12.8	12.9	12.7
GRAPHS						

Ferrous Alloys





Apr10/24