

OIL ANALYSIS REPORT

Area MIX ROOM C [98907493] KR-GR-003112 - EAST DUMPER (S/N MIX C - 11513062)

Hydraulic System

AW HYDRAULIC OIL ISO 68 (--- GAL)

DIAGNOSIS

Recommendation

We recommend you service the filters on this component if applicable. Resample at the next service interval to monitor. (Customer Sample Comment: 98907493)

Wear


All component wear rates are normal.

Contamination

There is a high amount of silt (particulates < 14 microns in size) present in the oil.

Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.




| SAMPLE INFORMA | ATION | method | limit/base | current | history1 | history2 |
|-----------------|-------|--------------|------------|-------------------|---------------------|----------------|
| Sample Number | | Client Info | | PCA0119591 | PCA0116666 | PCA0120391 |
| Sample Date | | Client Info | | 17 Apr 2024 | 11 Mar 2024 | 11 Mar 2024 |
| Machine Age h | nrs | Client Info | | 0 | 0 | 0 |
| Oil Age h | nrs | Client Info | | 0 | 0 | 0 |
| Oil Changed | | Client Info | | Not Changd | N/A | N/A |
| Sample Status | | | | ABNORMAL | ABNORMAL | ABNORMAL |
| CONTAMINATIO | N | method | limit/base | current | history1 | history2 |
| Water | | WC Method | >0.05 | NEG | NEG | NEG |
| WEAR METALS | | method | limit/base | current | history1 | history2 |
| Iron p | pm | ASTM D5185m | >20 | 8 | 9 | 7 |
| Chromium p | pm | ASTM D5185m | >20 | 10 | 8 | 8 |
| Nickel p | pm | ASTM D5185m | >20 | 0 | <1 | <1 |
| Titanium p | pm | ASTM D5185m | | <1 | <1 | <1 |
| Silver p | pm | ASTM D5185m | | 0 | 0 | 0 |
| Aluminum p | pm | ASTM D5185m | >20 | 2 | 3 | 3 |
| | | ASTM D5185m | >20 | 0 | <1 | <1 |
| | · | ASTM D5185m | >20 | <1 | <1 | <1 |
| | | ASTM D5185m | >20 | 0 | <1 | <1 |
| | | ASTM D5185m | | <1 | <1 | <1 |
| | | ASTM D5185m | | 0 | <1 | <1 |
| ADDITIVES | | method | limit/base | current | history1 | history2 |
| Boron p | pm | ASTM D5185m | 5 | 0 | 0 | 0 |
| Barium p | pm | ASTM D5185m | 5 | 0 | <1 | 0 |
| Molybdenum p | pm | ASTM D5185m | 5 | 0 | 0 | 0 |
| Manganese p | pm | ASTM D5185m | | 0 | <1 | 0 |
| Magnesium p | pm | ASTM D5185m | 25 | 0 | <1 | <1 |
| Calcium p | pm | ASTM D5185m | 200 | 6 | 6 | 5 |
| | | ASTM D5185m | 300 | 342 | 384 | 391 |
| | | ASTM D5185m | 370 | 2 | 6 | 6 |
| | | ASTM D5185m | 2500 | 506 | 431 | 432 |
| CONTAMINANTS | S | method | limit/base | current | history1 | history2 |
| Silicon p | pm | ASTM D5185m | >15 | 2 | 2 | 2 |
| | | ASTM D5185m | | 2 | <1 | <1 |
| | | ASTM D5185m | >20 | 2 | 4 | 3 |
| FLUID CLEANLIN | VESS | method | limit/base | current | history1 | history2 |
| Particles >4µm | | ASTM D7647 | >5000 | 124070 | 210426 | 174454 |
| Particles >6µm | | ASTM D7647 | >1300 | <u> </u> | 4 5717 | A 21031 |
| Particles >14µm | | ASTM D7647 | >160 | 86 | A 289 | 436 |
| Particles >21µm | | ASTM D7647 | >40 | 19 | 4 7 | <u> </u> |
| Particles >38µm | | ASTM D7647 | >10 | 1 | 1 | 3 |
| Particles >71µm | | ASTM D7647 | >3 | 0 | 0 | 1 |
| Oil Cleanliness | | ISO 4406 (c) | >19/17/14 | A 24/22/14 | ▲ 25/23/15 | ▲ 25/22/16 |
| | | method | limit/booo | | In the transmission | bioton/2 |
| FLUID DEGRADA | | methou | limit/base | current | history1 | history2 |
| | | ASTM D8045 | 0.57 | 0.124 | 0.09 | 0.07 |


Report Id: KRAKIR [WUSCAR] 06155846 (Generated: 04/24/2024 14:20:45) Rev: 1


Submitted By: Wilberto Pacheco Garcia



OIL ANALYSIS REPORT











| VISUAL | | method | limit/base | current | history1 | history2 |
|------------------|--------|-----------|------------|---------|----------|----------|
| White Metal | scalar | *Visual | NONE | NONE | NONE | NONE |
| Yellow Metal | scalar | *Visual | NONE | NONE | NONE | NONE |
| Precipitate | scalar | *Visual | NONE | NONE | NONE | NONE |
| Silt | scalar | *Visual | NONE | NONE | NONE | NONE |
| Debris | scalar | *Visual | NONE | NONE | LIGHT | NONE |
| Sand/Dirt | scalar | *Visual | NONE | NONE | NONE | NONE |
| Appearance | scalar | *Visual | NORML | NORML | NORML | NORML |
| Odor | scalar | *Visual | NORML | NORML | NORML | NORML |
| Emulsified Water | scalar | *Visual | >0.05 | NEG | NEG | NEG |
| Free Water | scalar | *Visual | | NEG | NEG | NEG |
| FLUID PROPE | RTIES | method | limit/base | current | history1 | history2 |
| Visc @ 40°C | cSt | ASTM D445 | 68 | 66.8 | 66.6 | 66.3 |
| SAMPLE IMAG | ES | method | limit/base | current | history1 | history2 |
| Color | | | | | | |
| Bottom | | | | | (18) | (|





Report Id: KRAKIR [WUSCAR] 06155846 (Generated: 04/24/2024 14:20:45) Rev: 1

Submitted By: Wilberto Pacheco Garcia

Page 2 of 2