


OIL ANALYSIS REPORT

Sample Rating Trend



MIX ROOM A [98858723]

KR-GR-003110 - REWORK DUMPER 15A (S/N MIX A - 11513052)

Hydraulic System

AW HYDRAULIC OIL ISO 68 (--- GAL)

DIAGNOSIS

Recommendation

No corrective action is recommended at this time. Resample at the next service interval to monitor. (Customer Sample Comment: 98858723)

All component wear rates are normal.

Contamination

There is a moderate amount of silt (particulates < 14 microns in size) present in the oil.


Fluid Condition


The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.


v2020 Apr2021 Smp2021 Mm2022 Smp2022 Mm2023 Ju2023 Nev2023						
SAMPLE INFORI	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		PCA0119592	PCA0116073	PCA0114832
Sample Date		Client Info		16 Apr 2024	11 Mar 2024	02 Jan 2024
Machine Age	hrs	Client Info		0	76768	76768
Oil Age	hrs	Client Info		0	76768	76768
Oil Changed		Client Info		Not Changd	N/A	N/A
Sample Status				ATTENTION	ATTENTION	ABNORMAL
CONTAMINAT	ION	method	limit/base	current	history1	history2
Water		WC Method	>0.05	NEG	NEG	NEG
WEAR METAL	S	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>20	<1	<1	1
Chromium	ppm	ASTM D5185m	>20	0	<1	<1
Nickel	ppm	ASTM D5185m	>20	0	0	0
Titanium	ppm	ASTM D5185m		0	<1	0
Silver	ppm	ASTM D5185m		0	0	0
Aluminum	ppm	ASTM D5185m	>20	0	3	1
Lead	ppm	ASTM D5185m	>20	0	<1	0
Copper	ppm	ASTM D5185m	>20	1	2	1
Tin	ppm	ASTM D5185m	>20	0	<1	<1
Vanadium	ppm	ASTM D5185m		<1	<1	0
Cadmium	ppm	ASTM D5185m		0	<1	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	5	0	0	0
Barium	ppm	ASTM D5185m	5	0	0	10
Molybdenum	ppm	ASTM D5185m	5	0	0	<1
Manganese	ppm	ASTM D5185m		0	0	0
Magnesium	ppm	ASTM D5185m	25	<1	0	0
Calcium	ppm	ASTM D5185m	200	<1	4	1
Phosphorus	ppm	ASTM D5185m	300	335	395	366
Zinc	ppm	ASTM D5185m	370	<1	4	0
Sulfur	ppm	ASTM D5185m	2500	627	553	522
CONTAMINAN	TS	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>15	2	2	1
Sodium	ppm	ASTM D5185m		<1	<1	0
Potassium	ppm	ASTM D5185m	>20	0	1	1
					'	·
FLUID CLEANL		method	limit/base	current	history1	history2
FLUID CLEANL		method ASTM D7647	limit/base >10000	current 19536	history1 13944	history2 ^ 22245
FLUID CLEANL Particles >4µm Particles >6µm		method ASTM D7647 ASTM D7647	limit/base >10000 >2500	current 19536 1886	history1 13944 479	history2 ▲ 22245 1204
FLUID CLEAND Particles >4μm Particles >6μm Particles >14μm		method ASTM D7647 ASTM D7647 ASTM D7647	limit/base >10000 >2500 >640	current 19536 1886 143	history1 13944 479 39	history2 22245 1204 60
FLUID CLEANI Particles >4μm Particles >6μm Particles >14μm Particles >21μm		method ASTM D7647 ASTM D7647 ASTM D7647 ASTM D7647	limit/base >10000 >2500 >640 >160	current 19536 1886 143 35	history1 13944 479 39 10	history2 22245 1204 60 11
FLUID CLEAND Particles >4μm Particles >6μm Particles >14μm Particles >21μm Particles >38μm		method ASTM D7647 ASTM D7647 ASTM D7647 ASTM D7647 ASTM D7647	limit/base >10000 >2500 >640 >160 >40	current 19536 1886 143 35	history1 13944 479 39 10 1	history2 22245 1204 60 11 0
FLUID CLEAND Particles >4μm Particles >6μm Particles >14μm Particles >21μm Particles >38μm Particles >71μm		method ASTM D7647 ASTM D7647 ASTM D7647 ASTM D7647 ASTM D7647 ASTM D7647	limit/base >10000 >2500 >640 >160 >40 >10	current 19536 1886 143 35 2 0	history1 13944 479 39 10 1	history2 22245 1204 60 11 0 0
FLUID CLEAND Particles >4μm Particles >6μm Particles >14μm Particles >21μm Particles >38μm		method ASTM D7647 ASTM D7647 ASTM D7647 ASTM D7647 ASTM D7647	limit/base >10000 >2500 >640 >160 >40	current 19536 1886 143 35	history1 13944 479 39 10 1	history2 22245 1204 60 11 0




OIL ANALYSIS REPORT











VISUAL						
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.05	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG
FLUID PROPE	RTIES	method	limit/hase	current	history1	history2

Visc @ 40°C	cSt	ASTM D445	68	67.0	66.9	66.5

Color

Bottom









Laboratory Sample No.

: PCA0119592 Lab Number : 06155870 Unique Number : 10991293

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 22 Apr 2024

Tested : 23 Apr 2024 Diagnosed : 24 Apr 2024 - Don Baldridge

KraftHeinz - Kirksville - Plant 8333 PCA 2504 INDUSTRIAL DR

KIRKSVILLE, MO US 63501

Test Package : IND 2 Certificate 12367 To discuss this sample report, contact Customer Service at 1-800-237-1369.

Contact: WALLACE WARD wallace.ward@kraftheinzcompany.com T: (660)627-1031

Submitted By: Wilberto Pacheco Garcia

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012) F: (660)627-5887