


OIL ANALYSIS REPORT

Sample Rating Trend



Machine Id **T307** Component **Transmission (Auto)** Fluid **COGNIS EMGARD 2805 ATF (36 hrs)**

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor. Please specify the component make and model with your next sample.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the fluid.


Fluid Condition

The condition of the fluid is acceptable for the time in service.

SAMPLE INFOR	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		PCA0102238	PCA0114718	PCA0107492
Sample Date		Client Info		11 Apr 2024	10 Jan 2024	11 Oct 2023
Machine Age	mls	Client Info		345460	316470	290899
Oil Age	mls	Client Info		75000	75000	75000
Oil Changed		Client Info		Not Changd	Changed	Not Changd
Sample Status				NORMAL	NORMAL	NORMAL
CONTAMINAT	ION	method	limit/base	current	history1	history2
Water		WC Method	>0.1	NEG	NEG	NEG
WEAR METAL	S	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>160	52	66	39
Chromium	ppm	ASTM D5185m	>5	<1	<1	<1
Nickel	ppm	ASTM D5185m	>5	0	<1	<1
Titanium	ppm	ASTM D5185m		<1	<1	0
Silver	ppm	ASTM D5185m	>5	0	0	0
Aluminum	ppm	ASTM D5185m	>50	8	12	9
Lead	ppm	ASTM D5185m	>50	4	14	10
Copper	ppm	ASTM D5185m	>225	17	41	25
Tin	ppm	ASTM D5185m	>10	1	2	<1
Vanadium	ppm	ASTM D5185m	-	<1	0	0
Cadmium	ppm	ASTM D5185m		<1	<1	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		81	117	81
Barium	ppm	ASTM D5185m		0	2	0
Molybdenum	ppm	ASTM D5185m		<1	<1	<1
Manganese	ppm	ASTM D5185m		<1	<1	0
Magnesium	ppm	ASTM D5185m		2	1	2
Calcium	ppm	ASTM D5185m		120	144	119
Phosphorus	ppm	ASTM D5185m		224	290	222
Zinc	ppm	ASTM D5185m		11	13	2
Sulfur	ppm	ASTM D5185m		2942	2147	1758
CONTAMINAN	ITS	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>20	10	5	3
Sodium	ppm	ASTM D5185m		3	0	3
Potassium	ppm	ASTM D5185m	>20	2	2	1
VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	LIGHT	NONE	NONE
	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	Jouran			NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate Silt		*Visual *Visual	NONE	NONE	NONE	NONE
Precipitate Silt Debris	scalar			NONE NONE		
Precipitate Silt	scalar scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate Silt Debris	scalar scalar scalar	*Visual *Visual	NONE NONE	NONE NONE	NONE NONE	NONE LIGHT
Precipitate Silt Debris Sand/Dirt	scalar scalar scalar scalar	*Visual *Visual *Visual	NONE NONE NONE	NONE NONE NONE	NONE NONE NONE	NONE LIGHT NONE
Precipitate Silt Debris Sand/Dirt Appearance	scalar scalar scalar scalar scalar	*Visual *Visual *Visual *Visual	NONE NONE NORML	NONE NONE NONE NORML	NONE NONE NONE NORML	NONE LIGHT NONE NORML
Precipitate Silt Debris Sand/Dirt Appearance Odor	scalar scalar scalar scalar scalar scalar	*Visual *Visual *Visual *Visual *Visual	NONE NONE NORML NORML	NONE NONE NORE NORML NORML	NONE NONE NORML NORML NEG NEG	NONE LIGHT NONE NORML NORML



OIL ANALYSIS REPORT



FLUID PROP	ERTIES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	38.9	33.2	31.6	31.3
SAMPLE IMA	GES	method	limit/base	current	history1	history2
Color				no image	no image	no image
Bottom				no image	no image	no image
GRAPHS						
Ferrous Allovs						

