




# OIL ANALYSIS REPORT

Sample Rating Trend



**NORMAL**



Machine Id  
**726018-5037**

Component  
**Diesel Engine**

Fluid  
**PETRO CANADA DURON SHP 15W40 (--- LTR)**

## DIAGNOSIS

### Recommendation

Resample at the next service interval to monitor.

### Wear

All component wear rates are normal.

### Contamination

There is no indication of any contamination in the oil.

### Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

## SAMPLE INFORMATION

	method	limit/base	current	history1	history2
Sample Number	Client Info		<b>GFL0058111</b>	GFL0058056	GFL0100157
Sample Date	Client Info		<b>18 Apr 2024</b>	27 Mar 2024	26 Dec 2023
Machine Age	hrs	Client Info	<b>18485</b>	18307	17919
Oil Age	hrs	Client Info	<b>566</b>	388	444
Oil Changed	Client Info		<b>Changed</b>	Not Changd	Changed
Sample Status			<b>NORMAL</b>	NORMAL	NORMAL

## CONTAMINATION

	method	limit/base	current	history1	history2
Fuel	WC Method	>5	<b>&lt;1.0</b>	<1.0	<1.0
Water	WC Method	>0.2	<b>NEG</b>	NEG	NEG
Glycol	WC Method		<b>NEG</b>	NEG	NEG

## WEAR METALS

	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m >110	<b>14</b>	11	5
Chromium	ppm	ASTM D5185m >4	<b>&lt;1</b>	<1	0
Nickel	ppm	ASTM D5185m >2	<b>&lt;1</b>	<1	0
Titanium	ppm	ASTM D5185m	<b>&lt;1</b>	0	0
Silver	ppm	ASTM D5185m >2	<b>&lt;1</b>	<1	0
Aluminum	ppm	ASTM D5185m >25	<b>3</b>	2	<1
Lead	ppm	ASTM D5185m >45	<b>1</b>	0	<1
Copper	ppm	ASTM D5185m >85	<b>2</b>	2	<1
Tin	ppm	ASTM D5185m >4	<b>1</b>	<1	0
Vanadium	ppm	ASTM D5185m	<b>&lt;1</b>	0	0
Cadmium	ppm	ASTM D5185m	<b>&lt;1</b>	0	0

## ADDITIVES

	method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m 0	<b>2</b>	5	3
Barium	ppm	ASTM D5185m 0	<b>0</b>	0	0
Molybdenum	ppm	ASTM D5185m 60	<b>61</b>	61	56
Manganese	ppm	ASTM D5185m 0	<b>&lt;1</b>	<1	0
Magnesium	ppm	ASTM D5185m 1010	<b>947</b>	968	928
Calcium	ppm	ASTM D5185m 1070	<b>1076</b>	1103	1080
Phosphorus	ppm	ASTM D5185m 1150	<b>1124</b>	1042	935
Zinc	ppm	ASTM D5185m 1270	<b>1266</b>	1278	1194
Sulfur	ppm	ASTM D5185m 2060	<b>3460</b>	3585	2730

## CONTAMINANTS

	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m >30	<b>6</b>	5	4
Sodium	ppm	ASTM D5185m	<b>2</b>	4	4
Potassium	ppm	ASTM D5185m >20	<b>3</b>	2	<1

## INFRA-RED




	method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844 >3	<b>0.6</b>	0.5	0.3
Nitration	Abs/cm	*ASTM D7624 >20	<b>7.1</b>	6.4	6.8
Sulfation	Abs/.1mm	*ASTM D7415 >30	<b>19.4</b>	18.7	18.9

## FLUID DEGRADATION

	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414 >25	<b>14.7</b>	14.1	14.7
Base Number (BN)	mg KOH/g	ASTM D2896 9.8	<b>8.6</b>	8.7	8.5







# OIL ANALYSIS REPORT



PARAMETER	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG

FLUID PROPERTIES	method	limit/base	current	history1	history2
Visc @ 100°C	cSt	ASTM D445	15.4	13.6	13.8

## GRAPHS



**Laboratory** : WearCheck USA - 501 Madison Ave., Cary, NC 27513  
**Sample No.** : GFL0058111      **Received** : 22 Apr 2024  
**Lab Number** : 06156706      **Tested** : 23 Apr 2024  
**Unique Number** : 10992129      **Diagnosed** : 23 Apr 2024 - Wes Davis  
**Test Package** : FLEET

**GFL Environmental - 657 - Charlottesville Hauling**  
 5498 Richmond Road  
 Troy, VA  
 US 22974  
 Contact: Brian Ulickas  
 bulickas@gflenv.com

To discuss this sample report, contact Customer Service at 1-800-237-1369.  
 \* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.  
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)