


# **OIL ANALYSIS REPORT**



Area (83J 44U) 913147 Diesel Engine

PETRO CANADA DURON SHP 15W40 (--- GAL)





# **DIAGNOSIS**

## Recommendation

Resample at the next service interval to monitor.

All component wear rates are normal.

## Contamination

There is no indication of any contamination in the oil.


# Fluid Condition


The oil viscosity is lower than normal. The BN result indicates that there is suitable alkalinity remaining in the oil. Confirm oil type.


N SHP 15W40 (	- GAL)	Feb 2023	Oct2023 Dec2023	Jan 2024 Mar 2024	Apr2024	
SAMPLE INFORI	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		GFL0118804	GFL0114173	GFL011412
Sample Date		Client Info		17 Apr 2024	26 Mar 2024	05 Mar 2024
Machine Age	hrs	Client Info		3243	3103	2970
Oil Age	hrs	Client Info		2970	0	1857
Oil Changed		Client Info		Not Changd	Not Changd	Changed
Sample Status				ATTENTION	ATTENTION	SEVERE
CONTAMINAT	ION	method	limit/base	current	history1	history2
Fuel		WC Method	>3.0	<1.0	0.2	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
WEAR METAL	S	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>120	6	2	15
Chromium	ppm	ASTM D5185m	>20	<1	0	<1
Nickel	ppm	ASTM D5185m	>5	3	2	<b>1</b> 1
Titanium	ppm	ASTM D5185m	>2	<1	0	0
Silver	ppm	ASTM D5185m	>2	<1	0	0
Aluminum	ppm	ASTM D5185m	>20	3	<1	<1
Lead	ppm	ASTM D5185m	>40	<1	<1	<1
Copper	ppm	ASTM D5185m	>330	2	<1	5
Tin	ppm	ASTM D5185m	>15	1	0	0
Vanadium	ppm	ASTM D5185m		<1	<1	0
Cadmium	ppm	ASTM D5185m		<1	0	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	0	40	57	15
Barium	ppm	ASTM D5185m	0	0	0	0
Molybdenum	ppm	ASTM D5185m	60	58	55	58
Manganese	ppm	ASTM D5185m	0	<1	0	<1
Magnesium	ppm	ASTM D5185m	1010	1038	1142	1130
Calcium	ppm	ASTM D5185m	1070	813	872	913
Phosphorus	ppm	ASTM D5185m	1150	1058	960	1032
Zinc	ppm	ASTM D5185m	1270	1199	1299	1296
Sulfur	ppm	ASTM D5185m	2060	3392	3975	3674
CONTAMINAN	TS	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	5	4	6
Sodium	ppm	ASTM D5185m		3	4	7
-						
	ppm	ASTM D5185m	>20	2	<1	2
	ppm	ASTM D5185m method	>20 limit/base	2 current	<1 history1	
Potassium INFRA-RED	ppm %					
Potassium INFRA-RED Soot %		method	limit/base	current	history1	history2
Potassium  INFRA-RED  Soot %  Nitration	%	method *ASTM D7844	limit/base	current 0.2	history1	history2
Potassium  INFRA-RED  Soot %  Nitration	% Abs/cm Abs/.1mm	method  *ASTM D7844  *ASTM D7624  *ASTM D7415	limit/base >4 >20	0.2 8.1	history1 0.2 7.3	0.4 10.1 20.7
Potassium  INFRA-RED  Soot %  Nitration  Sulfation	% Abs/cm Abs/.1mm	method  *ASTM D7844  *ASTM D7624  *ASTM D7415	limit/base	current 0.2 8.1 19.9	history1  0.2  7.3  19.1	0.4 10.1




# **OIL ANALYSIS REPORT**













FLUID FROF	EULIES					
Visc @ 100°C	cSt	ASTM D445	15.4	<b>11.7</b>	11.6	12.2

## **GRAPHS**













Certificate 12367

Sample No.

: GFL0118804 Lab Number : 06156725 Unique Number : 10992148 Test Package : FLEET

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 22 Apr 2024 **Tested** Diagnosed

: 23 Apr 2024 : 24 Apr 2024 - Sean Felton

GFL Environmental - 836 - Kansas City Hauling

7801 East Truman Road Kansas City, MO US 64126

Contact: Loyce Stewart loyce.stewart@gflenv.com

To discuss this sample report, contact Customer Service at 1-800-237-1369. \* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:

F: