


OIL ANALYSIS REPORT







DT794 Component
Diesel Engine

Machine Id

PETRO CANADA DURON SHP 10W30 (40

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

All component wear rates are normal.

Contamination

There is no indication of any contamination in the


Fluid Condition


The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.


QTS)		Mar202	2 Sep 2022	0ct2023 Ap	072024	
SAMPLE INFOR	RMATION	method	limit/base	current	history1	history2
Sample Number		Client Info		PCA0091265	PCA0103331	PCA0074868
Sample Date		Client Info		18 Apr 2024	04 Oct 2023	06 Sep 2022
Machine Age	mls	Client Info		154564	129851	76946
Oil Age	mls	Client Info		129851	52905	0
Oil Changed		Client Info		Changed	Changed	Changed
Sample Status				NORMAL	NORMAL	NORMAL
CONTAMINAT	TION	method	limit/base	current	history1	history2
Fuel		WC Method	>5	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method	7 7.2	NEG	NEG	NEG
WEAR METAL	_S	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>110	17	17	25
Chromium	ppm	ASTM D5185m	>4	<1	<1	<1
Nickel	ppm	ASTM D5185m	>2	0	<1	0
Titanium	ppm	ASTM D5185m		0	0	0
Silver	ppm	ASTM D5185m	>2	0	0	<1
Aluminum	ppm	ASTM D5185m	>25	8	1	16
Lead	ppm	ASTM D5185m	>45	0	<1	0
Copper	ppm	ASTM D5185m	>85	2	2	4
Tin	ppm	ASTM D5185m	>4	0	<1	0
Antimony	ppm	ASTM D5185m				
Vanadium	ppm	ASTM D5185m		0	0	0
Cadmium	ppm	ASTM D5185m		0	0	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	2	5	3	0
Barium	ppm	ASTM D5185m	0	0	0	0
Molybdenum	ppm	ASTM D5185m	50	67	64	68
Manganese	ppm	ASTM D5185m	0	<1	<1	<1
Magnesium	ppm	ASTM D5185m	950	988	923	934
Calcium	ppm	ASTM D5185m	1050	1180	1174	1143
Phosphorus	ppm	ASTM D5185m	995	1057	1033	1029
Zinc	ppm	ASTM D5185m	1180	1320	1307	1272
Sulfur	ppm	ASTM D5185m	2600	3112	2727	2653
CONTAMINAN	NTS	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>30	6	7	6
Sodium	ppm	ASTM D5185m		1	0	1
Potassium	ppm	ASTM D5185m	>20	8	30	36
INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844	>3	0.7	0.8	0.8
Nitration	Abs/cm	*ASTM D7624	>20	9.7	10.1	11.1
Sulfation	Abs/.1mm	*ASTM D7415	>30	22.9	23.3	25.0
FLUID DEGRA	DATION	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414	>25	18.9	19.4	20.3
Base Number (BN)	mg KOH/g			5.5	4.9	6.6
2000 Hamber (B14)	mg norng	. IO I III DE000		0.0	1.0	0.0




OIL ANALYSIS REPORT













FLUID PROPI	EHILO	method			riistory i	nistoryz
Visc @ 100°C	cSt	ASTM D445	12.00	10.9	11.6	11.5

GRAPHS













Certificate 12367

Laboratory Sample No. Lab Number : 06158333 Unique Number : 10993756

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 : PCA0091265

Test Package : FLEET

Received : 23 Apr 2024 **Tested** : 24 Apr 2024

Diagnosed : 24 Apr 2024 - Wes Davis

NW WHITE & CO - ANDERSON DIVISION

2605 RIVER RD PIEDMONT, SC US 29673

Contact: James Threatt jthreatt@nwwhite.com T: (864)918-4646

To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Report Id: NWWPIE [WUSCAR] 06158333 (Generated: 04/25/2024 15:03:41) Rev: 1