OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL

Machine Id
DT760
Component
Rear Differential
Fluid
CHEVRON DELO SYNTHETIC GEAR 75W90 (--- QTS)

DIAGNOSIS

Recommendation
Resample at the next service interval to monitor.

Wear
All component wear rates are normal.

Contamination
There is no indication of any contamination in the oil.

Fluid Condition
The condition of the oil is acceptable for the time in service.

SAMPLE INFORMATION		method	limit/base	current	history1	history2
Sample Number		Client Info		**PCA0091258**	PCA0103251	PCA0091250
Sample Date		Client Info		**17 Apr 2024**	15 Sep 2023	28 Mar 2023
Machine Age	mls	Client Info		**179366**	152645	127511
Oil Age	mls	Client Info		**0**	76300	0
Oil Changed		Client Info		**Not Changd**	Changed	Not Changd
Sample Status				**NORMAL**	NORMAL	ABNORMAL

CONTAMINATION		method	limit/base	current	history1	history2
Water		WC Method	>.2	**NEG**	NEG	NEG

WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>1200	**111**	169	144
Chromium	ppm	ASTM D5185m	>8	**1**	1	<1
Nickel	ppm	ASTM D5185m	>20	**5**	7	7
Titanium	ppm	ASTM D5185m	>4	**<1**	<1	0
Silver	ppm	ASTM D5185m		**0**	<1	0
Aluminum	ppm	ASTM D5185m	>30	**2**	5	2
Lead	ppm	ASTM D5185m	>25	**<1**	0	0
Copper	ppm	ASTM D5185m	>50	**2**	<1	0
Tin	ppm	ASTM D5185m	>5	**<1**	0	0
Vanadium	ppm	ASTM D5185m		**<1**	0	0
Cadmium	ppm	ASTM D5185m		**<1**	0	0

ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		**240**	215	207
Barium	ppm	ASTM D5185m		**1**	0	0
Molybdenum	ppm	ASTM D5185m		**21**	12	12
Manganese	ppm	ASTM D5185m		**1**	2	2
Magnesium	ppm	ASTM D5185m		**157**	107	106
Calcium	ppm	ASTM D5185m		**306**	180	171
Phosphorus	ppm	ASTM D5185m		**1271**	1404	1350
Zinc	ppm	ASTM D5185m		**267**	149	156
Sulfur	ppm	ASTM D5185m		**20181**	26783	25056

CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>230	**50**	103	100
Sodium	ppm	ASTM D5185m		**1**	2	0
Potassium	ppm	ASTM D5185m	>20	**<1**	1	<1

VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	**NONE**	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	**NONE**	NONE	NONE
Precipitate	scalar	*Visual	NONE	**NONE**	NONE	NONE
Silt	scalar	*Visual	NONE	**NONE**	NONE	NONE
Debris	scalar	*Visual	NONE	**NONE**	NONE	▲ MODER
Sand/Dirt	scalar	*Visual	NONE	**NONE**	NONE	NONE
Appearance	scalar	*Visual	NORML	**NORML**	NORML	NORML
Odor	scalar	*Visual	NORML	**NORML**	NORML	NORML
Emulsified Water	scalar	*Visual	>.2	**NEG**	NEG	NEG
Free Water	scalar	*Visual		**NEG**	NEG	NEG

OIL ANALYSIS REPORT



FLUID PROPERTIES		method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	106	**74.8**	83.7	86.0

SAMPLE IMAGES	method	limit/base	current	history1	history2
Color			*no image*	*no image*	*no image*
Bottom			*no image*	*no image*	*no image*

GRAPHS

Ferrous Alloys



Non-ferrous Metals



Viscosity @ 40°C



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : PCA0091258
Lab Number : 06158584
Unique Number : 10994007
Test Package : FLEET

Received : 23 Apr 2024
Tested : 25 Apr 2024
Diagnosed : 25 Apr 2024 - Wes Davis

To discuss this sample report, contact Customer Service at 1-800-237-1369.
** - Denotes test methods that are outside of the ISO 17025 scope of accreditation.*
Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

NW WHITE & CO - ANDERSON DIVISION
2605 RIVER RD
PIEDMONT, SC
US 29673
Contact: James Threatt
jthreatt@nwwhite.com
T: (864)918-4646
F: