

OIL ANALYSIS REPORT

Sample Rating Trend



Machine Id BM-223 Component Diesel Engine Fluid

PETRO CANADA DURON SHP 10W30 (10 GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

Metal levels are typical for a components first oil change.

Contamination

Elevated aluminum (Al) and/or lead (Pb) and potassium (K) levels in your metals analysis are likely a result of solder flux release into the lubricant and is common on new equipment/components. There is no indication of any contamination in the oil.

Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.


GAL)				Apicoza		
SAMPLE INFOR	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		PCA0117749		
Sample Date		Client Info		15 Apr 2024		
Machine Age	mls	Client Info		16839		
Oil Age	mls	Client Info		16839		
Oil Changed	iiiio	Client Info		Changed		
Sample Status				NORMAL		
CONTAMINAT		method	limit/base	-	_	history2
	ION			current	history1	TIISTOL A
Fuel		WC Method	>5	<1.0		
Water		WC Method	>0.2	NEG		
Glycol		WC Method		NEG		
WEAR METAL	.S	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>100	54		
Chromium	ppm	ASTM D5185m	>20	0		
Nickel	ppm	ASTM D5185m	>4	0		
Titanium	ppm	ASTM D5185m		0		
Silver	ppm	ASTM D5185m	>3	0		
Aluminum	ppm	ASTM D5185m	>20	11		
Lead	ppm	ASTM D5185m	>40	0		
Copper	ppm	ASTM D5185m	>330	12		
Tin	ppm	ASTM D5185m	>15	<1		
Vanadium	ppm	ASTM D5185m		0		
Cadmium	ppm	ASTM D5185m		0		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	2	25		
Barium	ppm	ASTM D5185m	0	<1		
Molybdenum	ppm	ASTM D5185m	50	11		
Manganese	ppm	ASTM D5185m	0	1		
Magnesium	ppm	ASTM D5185m	950	839		
Calcium	ppm	ASTM D5185m	1050	1486		
Phosphorus	ppm	ASTM D5185m	995	875		
Zinc	ppm	ASTM D5185m	1180	1020		
Sulfur	ppm	ASTM D5185m	2600	3732		
CONTAMINAN	ITS	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	17		
Sodium	ppm	ASTM D5185m		2		
Potassium	ppm	ASTM D5185m	>20	44		
INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844	>3	0.3		
Nitration	Abs/cm	*ASTM D7624	>20	10.5		
Sulfation	Abs/.1mm	*ASTM D7415	>30	23.0		
FLUID DEGRA	DATION	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414	>25	18.2		
Base Number (BN)	mg KOH/g	ASTM D2896		5.7		





Abnorma

8 Apr15/24

OIL ANALYSIS REPORT







To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Report Id: BLUCHA [WUSCAR] 06158712 (Generated: 04/25/2024 10:33:01) Rev: 1

Certificate 12367

Submitted By: Jody Greer

T: (980)225-9968

F: (704)588-2901

Page 2 of 2