


OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL



Machine Id
408
 Component
Diesel Engine
 Fluid
RED GIANT LOCOMOTIVE EO 20W40 (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor. Please specify the component make and model with your next sample.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

SAMPLE INFORMATION		method	limit/base	current	history1	history2
Sample Number	Client Info			PCA0092705	PCA05995910	---
Sample Date	Client Info			19 Apr 2024	23 Oct 2023	---
Machine Age	hrs	Client Info		0	0	---
Oil Age	hrs	Client Info		0	0	---
Oil Changed	Client Info			N/A	N/A	---
Sample Status				NORMAL	NORMAL	---

CONTAMINATION		method	limit/base	current	history1	history2
Fuel	WC Method	>5		<1.0	<1.0	---
Water	WC Method	>0.2		NEG	NEG	---
Glycol	WC Method			NEG	NEG	---

WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>100	45	31	---
Chromium	ppm	ASTM D5185m	>20	3	3	---
Nickel	ppm	ASTM D5185m	>4	2	2	---
Titanium	ppm	ASTM D5185m		<1	<1	---
Silver	ppm	ASTM D5185m	>3	0	0	---
Aluminum	ppm	ASTM D5185m	>20	4	3	---
Lead	ppm	ASTM D5185m	>40	9	10	---
Copper	ppm	ASTM D5185m	>330	25	24	---
Tin	ppm	ASTM D5185m	>15	13	14	---
Vanadium	ppm	ASTM D5185m		<1	<1	---
Cadmium	ppm	ASTM D5185m		<1	<1	---




ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		40	35	---
Barium	ppm	ASTM D5185m		0	<1	---
Molybdenum	ppm	ASTM D5185m		45	45	---
Manganese	ppm	ASTM D5185m		<1	<1	---
Magnesium	ppm	ASTM D5185m		9	10	---
Calcium	ppm	ASTM D5185m		3387	3225	---
Phosphorus	ppm	ASTM D5185m	0	10	4	---
Zinc	ppm	ASTM D5185m	0	3	0	---
Sulfur	ppm	ASTM D5185m	1900	3140	3477	---

CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	6	8	---
Sodium	ppm	ASTM D5185m		19	18	---
Potassium	ppm	ASTM D5185m	>20	2	3	---

INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844	>3	1.2	0.9	---
Nitration	Abs/cm	*ASTM D7624	>20	8.7	8.3	---
Sulfation	Abs/.1mm	*ASTM D7415	>30	17.6	15.9	---

FLUID DEGRADATION		method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414	>25	7.7	7.4	---
Base Number (BN)	mg KOH/g	ASTM D2896	11	9.41	11.04	---









OIL ANALYSIS REPORT



VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	---
Yellow Metal	scalar	*Visual	NONE	NONE	---
Precipitate	scalar	*Visual	NONE	NONE	---
Silt	scalar	*Visual	NONE	NONE	---
Debris	scalar	*Visual	NONE	NONE	---
Sand/Dirt	scalar	*Visual	NONE	NONE	---
Appearance	scalar	*Visual	NORML	NORML	---
Odor	scalar	*Visual	NORML	NORML	---
Emulsified Water	scalar	*Visual	>0.2	NEG	---
Free Water	scalar	*Visual		NEG	---

FLUID PROPERTIES	method	limit/base	current	history1	history2	
Visc @ 100°C	cSt	ASTM D445	15.4	14.8	14.4	---

GRAPHS



Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : PCA0092705 **Received** : 24 Apr 2024
Lab Number : **06159326** **Tested** : 25 Apr 2024
Unique Number : 10994749 **Diagnosed** : 25 Apr 2024 - Wes Davis
Test Package : MOB 2

U.S. SUGAR CORP
 1731 S W.C. OWEN AVENUE
 CLEWISTON, FL
 US 33440-3032
 Contact: JAMES MCGROGAN
 jmcgrogan@ussugar.com

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)