


OIL ANALYSIS REPORT



(YA172344) GFL035 922035 Diesel Engine

DIESEL ENGINE OIL SAE 40 (42 QTS)





DIAGNOSIS

Recommendation

Resample at the next service interval to monitor. Please specify the brand, type, and viscosity of the oil on your next sample.

All component wear rates are normal.

Contamination

There is no indication of any contamination in the


Fluid Condition


The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.


JAL 40 (42 Q10)						
SAMPLE INFORT	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		GFL0116465	GFL0102336	GFL0102288
Sample Date		Client Info		25 Apr 2024	01 Feb 2024	15 Sep 2023
Machine Age	hrs	Client Info		0	0	0
Oil Age	hrs	Client Info		600	600	600
Oil Changed		Client Info		Changed	Changed	Changed
Sample Status				NORMAL	NORMAL	NORMAL
CONTAMINAT	ION	method	limit/base	current	history1	history2
Fuel		WC Method	>3.0	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
WEAR METAL	S	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>120	57	9	10
Chromium	ppm	ASTM D5185m	>20	1	<1	<1
Nickel	ppm	ASTM D5185m	>5	<1	1	1
Titanium	ppm	ASTM D5185m	>2	0	0	<1
Silver	ppm	ASTM D5185m	>2	0	0	0
Aluminum	ppm	ASTM D5185m	>20	2	2	1
Lead	ppm	ASTM D5185m	>40	<1	0	0
Copper	ppm	ASTM D5185m	>330	3	1	3
Tin	ppm	ASTM D5185m	>15	1	<1	<1
Vanadium	ppm	ASTM D5185m		0	0	0
Cadmium	ppm	ASTM D5185m		0	0	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	250	0	0	4
Barium	ppm	ASTM D5185m	10	0	<1	0
Molybdenum	ppm	ASTM D5185m	100	61	64	66
Manganese	ppm	ASTM D5185m		<1	<1	0
Magnesium	ppm	ASTM D5185m	450	980	973	889
Calcium	ppm	ASTM D5185m	3000	1117	1094	1139
Phosphorus	ppm	ASTM D5185m	1150	992	1034	937
Zinc	ppm	ASTM D5185m	1350	1272	1287	1196
Sulfur	ppm	ASTM D5185m	4250	3187	2764	3057
CONTAMINAN	TS	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	5	2	4
Sodium	ppm	ASTM D5185m	>216	4	2	1
Potassium	ppm	ASTM D5185m	>20	<1	1	3
INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844	>4	1	0.8	0.6
Nitration	Abs/cm	*ASTM D7624	>20	8.8	8.6	7.5
Sulfation	Abs/.1mm	*ASTM D7415	>30	20.6	20.5	19.9
FLUID DEGRADATION method limit/base current history1 history2						
Oxidation	Abs/.1mm	*ASTM D7414	>25	16.5	16.1	15.0
Base Number (BN)	mg KOH/g	ASTM D2896	8.5	7.1	7.3	7.8
()	0 - 0					



OIL ANALYSIS REPORT










VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG


FLUID PROPERTIES		method				history2	
Visc @ 100°C	cSt	ASTM D445	14.4	14.0	13.8	13.5	

GRAPHS













Certificate 12367

Laboratory Sample No. Lab Number : 06161150

: GFL0116465 Unique Number : 10996573

Test Package : FLEET

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 26 Apr 2024

Tested : 26 Apr 2024 Diagnosed : 26 Apr 2024 - Wes Davis

GFL Environmental - 035 - Greensboro 1236 Elon Place High Point, NC US 27263

Contact: JORGE COSTA jorge.costa@gflenv.com T: (336)668-3712

To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)