

OIL ANALYSIS REPORT

Sample Rating Trend





Area G.LOPES CONSTRUCTION INC./Off-Road L33

Component Rear Left Final Drive

Fluid {not provided} (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor. Please specify the brand, type, and viscosity of the oil on your next sample.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.


Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

SAMPLE INFORM	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		PCA0122694		
Sample Date		Client Info		23 Apr 2024		
Machine Age	hrs	Client Info		11001		
Oil Age	hrs	Client Info		11001		
Oil Changed		Client Info		N/A		
Sample Status				NORMAL		
CONTAMINAT	ON	method	limit/base	current	history1	history2
Water		WC Method	>0.2	NEG		
WEAR METAL	S	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>800	48		
Chromium	ppm	ASTM D5185m	>10	<1		
Nickel	ppm	ASTM D5185m	>5	0		
Titanium	ppm	ASTM D5185m	>15	<1		
Silver	ppm	ASTM D5185m	>2	0		
Aluminum	ppm	ASTM D5185m	>75	2		
Lead	ppm	ASTM D5185m	>10	0		
Copper	ppm	ASTM D5185m	>75	11		
Tin	ppm	ASTM D5185m	>8	0		
Vanadium	ppm	ASTM D5185m		0		
Cadmium	ppm	ASTM D5185m		0		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		<1		
Barium	ppm	ASTM D5185m		0		
Molybdenum	ppm	ASTM D5185m		2		
Manganese	ppm	ASTM D5185m		1		
Magnesium	ppm	ASTM D5185m		21		
Calcium	ppm	ASTM D5185m		2755		
Phosphorus	ppm	ASTM D5185m		989		
Zinc	ppm	ASTM D5185m		1192		
Sulfur	ppm	ASTM D5185m		6174		
CONTAMINAN	TS	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>400	8		
Sodium	ppm	ASTM D5185m		2		
Potassium	ppm	ASTM D5185m	>20	0		
FLUID DEGRAD	DATION	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045		1.56		



OIL ANALYSIS REPORT



	VISUAL		method	limit/base	current	history1	history2
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
	Precipitate	scalar	*Visual	NONE	NONE		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
3/24	Appearance	scalar	*Visual	NORML	NORML		
Apr23/24	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>0.2	NEG		
	Free Water	scalar	*Visual		NEG		
	FLUID PROP		method	limit/base	current	history1	history2
	Visc @ 40°C	cSt	ASTM D445		196		
	SAMPLE IMA	GES	method	limit/base	current	history1	history2
Apr23/24 +	Color				no image	no image	no image
	Bottom				no image	no image	no image
	GRAPHS						
	Iron (ppm)				Lead (ppm)		
	Severe						
	E 1000 - Abnormal			udd 1	10 - Abnormal		
	0				0		
	Apr23/24			Apr23/24	Apr23/24		Δη/23/24
				Ap			Δ Δ
	Aluminum (ppm))			Chromium (p	pm)	
	200 Severe				30 Severe		
	a 100 Abnormal			u d	Abnormal		
	0						
	3/24				3/24		. 10
	Apr23/24			Apr23/24	Apr23/24		An62304
	Copper (ppm)				Silicon (ppm)		
	200 Severe			100	⁰⁰ Severe		
	톱 100 - Abnormal			틆 50	00 - Abnormal		
	0			4	0		4
	Apr23/2 [,]			Apr23/24	Apr23/2		40.22.04
							4
	Viscosity @ 40°C			B/H0	Acid Number		
				, and a second			
	(00 150 - Abnormal			in 1	.0		
	50			3/24 Acid Number (mg KOH/g) Acid Number (mg KOH/g) 2	.04		
	Apr23/24			Apr23/24 Aci	Apr23/24		An/23/24
Laboratory Sample No. Lab Number Unique Number	: WearCheck USA - 5 : PCA0122694 : <mark>06161661</mark> : 10997084	01 Madisor Receiv Testeo Diagn	ved : 26 d : 29			G LOPES CONSTRUCTION 565 WINTHROP S ⁻ TAUNTON, M/ US 02780	
tificate 12367 Test Package discuss this sample report, Denotes test methods that	, contact Customer Ser are outside of the ISO	vice at 1-80 17025 scop	00-237-1369 pe of accred	9. litation.	-	bmcgrat	CH MCGRATH h@glopes.com T:
tements of conformity to sp 6161661 (Generated: 04/29/202		on the sim	ipie accepta	nce decisior	i ruie (JCGM 10	6:2012) Submitted By:	F: MATT MANOL

Report Id: GLOTAU [WUSCAR] 06161661 (Generated: 04/29/2024 14:37:29) Rev: 1

Page 2 of 2