

## **OIL ANALYSIS REPORT**

Sample Rating Trend





DT863 Component Rear Differential Fluid GEAR OIL SAE 75W90 (--- GAL)

# DIAGNOSIS

**Recommendation** Resample at the next service interval to monitor.

The fluid was not specified, however, a fluid match indicates that this fluid is (GENERIC) GEAR OIL SAE 75W90. Please confirm.

### Wear

All component wear rates are normal.

### Contamination

There is no indication of any contamination in the oil.


#### Fluid Condition

The condition of the oil is acceptable for the time in service.

SAMPLE INFOR	MATION	method	limit/base	current	history1	history2		
Sample Number		Client Info		PCA0125440				
Sample Date		Client Info		07 May 2024				
Machine Age	mls	Client Info		51471				
Oil Age	mls	Client Info		0				
Oil Changed		Client Info		Not Changd				
Sample Status				NORMAL				
CONTAMINAT	ION	method	limit/base	current	history1	history2		
Water		WC Method	>.2	NEG				
WEAR METAL	.S	method	limit/base	current	history1	history2		
Iron	ppm	ASTM D5185m	>1200	230				
Chromium	ppm	ASTM D5185m	>8	2				
Nickel	ppm	ASTM D5185m	>20	8				
Titanium	ppm	ASTM D5185m		<1				
Silver	ppm	ASTM D5185m		0				
Aluminum	ppm	ASTM D5185m	>30	7				
Lead	ppm	ASTM D5185m	>25	0				
Copper	ppm	ASTM D5185m	>50	1				
Tin		ASTM D5185m	>50 >5	، <1				
Vanadium	ppm	ASTM D5185m	>0	<1				
vanadium Cadmium	ppm							
	ppm	ASTM D5185m		<1				
ADDITIVES		method	limit/base		history1	history2		
Boron	ppm	ASTM D5185m	400	201				
Barium	ppm	ASTM D5185m	200	1				
Molybdenum	ppm	ASTM D5185m	12	<1				
Manganese	ppm	ASTM D5185m		4				
Magnesium	ppm	ASTM D5185m	12	2				
Calcium	ppm	ASTM D5185m	150	27				
Phosphorus	ppm	ASTM D5185m	1650	1126				
Zinc	ppm	ASTM D5185m	125	11				
Sulfur	ppm	ASTM D5185m	22500	26333				
CONTAMINAN	ITS	method	limit/base	current	history1	history2		
Silicon	ppm	ASTM D5185m	>230	184				
Sodium	ppm	ASTM D5185m		4				
Potassium	ppm	ASTM D5185m	>20	3				
VISUAL		method	limit/base	current	history1	history2		
White Metal	scalar	*Visual	NONE	NONE				
Yellow Metal	scalar	*Visual	NONE	NONE				
Precipitate	scalar	*Visual	NONE	NONE				
Silt	scalar	*Visual	NONE	NONE				
Debris	scalar	*Visual	NONE	NONE				
Sand/Dirt	scalar	*Visual	NONE	NONE				
Appearance	scalar	*Visual	NORML	NORML				
Odor	scalar	*Visual	NORML	NORML				
Emulsified Water	scalar	*Visual	>.2	NEG				
Free Water	scalar	*Visual		NEG				
:50:11) Rev: 1	- Journal					Submitted By: Paul Riddic		



## **OIL ANALYSIS REPORT**



FLUID PROPE	RTIES	method	limit/base	current	history1	history
Visc @ 40°C	cSt A	STM D445	109	97.2		
SAMPLE IMAG	ies 🛛	method	limit/base	current	history1	history
Color				no image	no image	no image
Bottom				no image	no image	no image
Dottom				no imago	no imago	no inago
GRAPHS						
Ferrous Alloys			1			
200 - newspace chromium						
150-						
튭 100 -						
50 -						
0						
May7/24			May7/24			
– Non-ferrous Metal	S					
9 copper						
8 tin						
6 <u>E</u> 5						
4						
3						
May7/24			May7/24			
Viscosity @ 40°C						
130 - Abnormal						
125						
115						
3110 - <b>Base</b>						
95						
90 - 85 - Abnormal						
80						
May7/24			May7/24			
: WearCheck USA - 50				NW WH	ITE & CO - COLU	
: PCA0125440 : 06174395	Receive Tested		May 2024 May 2024		100 INDEPEN	IDENCE BL OLUMBIA,
11020448	Diagnos		May 2024 - V	Ves Davis		US 292



Unique Number : 11020448 Diagnosed : 10 May 2024 - Wes Davis Test Package : FLEET Contact: GEORGE EDWARDS Certificate L2367 To discuss this sample report, contact Customer Service at 1-800-237-1369. gedwards@nwwhite.com \* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Report Id: NWWCOL [WUSCAR] 06174395 (Generated: 05/11/2024 21:50:11) Rev: 1

US 29210

T:

F: