




# OIL ANALYSIS REPORT

Sample Rating Trend



**NORMAL**



Machine Id  
**382M**  
 Component  
**Diesel Engine**  
 Fluid  
**PETRO CANADA DURON SHP 15W40 (--- GAL)**

## DIAGNOSIS

### Recommendation

Resample at the next service interval to monitor.

### Wear

All component wear rates are normal.

### Contamination

There is no indication of any contamination in the oil.

### Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

## SAMPLE INFORMATION

	method	limit/base	current	history1	history2
Sample Number	Client Info		<b>GFL0117566</b>	GFL0108828	GFL0101544
Sample Date	Client Info		<b>07 May 2024</b>	29 Jan 2024	17 Nov 2023
Machine Age	hrs	Client Info	<b>17593</b>	16748	15958
Oil Age	hrs	Client Info	<b>16748</b>	600	11918
Oil Changed	Client Info		<b>Not Changed</b>	Changed	Changed
Sample Status			<b>NORMAL</b>	NORMAL	NORMAL

## CONTAMINATION

	method	limit/base	current	history1	history2
Fuel	WC Method	>3.0	<b>&lt;1.0</b>	<1.0	<1.0
Water	WC Method	>0.2	<b>NEG</b>	NEG	NEG
Glycol	WC Method		<b>NEG</b>	NEG	NEG

## WEAR METALS

	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m >120	<b>7</b>	10	6
Chromium	ppm	ASTM D5185m >20	<b>0</b>	<1	<1
Nickel	ppm	ASTM D5185m >5	<b>0</b>	<1	<1
Titanium	ppm	ASTM D5185m >2	<b>0</b>	0	<1
Silver	ppm	ASTM D5185m >2	<b>0</b>	0	0
Aluminum	ppm	ASTM D5185m >20	<b>1</b>	3	2
Lead	ppm	ASTM D5185m >40	<b>&lt;1</b>	<1	1
Copper	ppm	ASTM D5185m >330	<b>0</b>	<1	<1
Tin	ppm	ASTM D5185m >15	<b>&lt;1</b>	<1	<1
Vanadium	ppm	ASTM D5185m	<b>0</b>	0	0
Cadmium	ppm	ASTM D5185m	<b>0</b>	0	<1

## ADDITIVES

	method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m 0	<b>1</b>	2	<1
Barium	ppm	ASTM D5185m 0	<b>0</b>	<1	9
Molybdenum	ppm	ASTM D5185m 60	<b>59</b>	58	62
Manganese	ppm	ASTM D5185m 0	<b>&lt;1</b>	<1	<1
Magnesium	ppm	ASTM D5185m 1010	<b>931</b>	926	893
Calcium	ppm	ASTM D5185m 1070	<b>1061</b>	1011	1106
Phosphorus	ppm	ASTM D5185m 1150	<b>1024</b>	941	974
Zinc	ppm	ASTM D5185m 1270	<b>1223</b>	1219	1190
Sulfur	ppm	ASTM D5185m 2060	<b>3048</b>	2363	2881

## CONTAMINANTS

	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m >25	<b>4</b>	5	5
Sodium	ppm	ASTM D5185m	<b>3</b>	3	<1
Potassium	ppm	ASTM D5185m >20	<b>1</b>	2	3

## INFRA-RED




	method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844 >4	<b>0.7</b>	0.8	0.4
Nitration	Abs/cm	*ASTM D7624 >20	<b>7.9</b>	9.4	7.3
Sulfation	Abs/.1mm	*ASTM D7415 >30	<b>20.1</b>	21.6	19.5

## FLUID DEGRADATION

	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414 >25	<b>15.5</b>	17.3	15.3
Base Number (BN)	mg KOH/g	ASTM D2896 9.8	<b>7.5</b>	6.0	7.9







# OIL ANALYSIS REPORT



VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG

FLUID PROPERTIES	method	limit/base	current	history1	history2
Visc @ 100°C	cSt	ASTM D445	15.4	14.1	14.0

## GRAPHS



**Laboratory** : WearCheck USA - 501 Madison Ave., Cary, NC 27513  
**Sample No.** : GFL0117566      **Received** : 10 May 2024  
**Lab Number** : 06175193      **Tested** : 11 May 2024  
**Unique Number** : 11021246      **Diagnosed** : 11 May 2024 - Wes Davis  
**Test Package** : FLEET

**GFL Environmental - 415 - Michigan East**  
 6200 Elmridge  
 Sterling Heights, MI  
 US 48313  
 Contact: Frank Wolak  
 fwolak@gflenv.com  
 T: (586)825-9514  
 F:

To discuss this sample report, CONTACT Customer Service at 1-800-237-1369.  
 \* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.  
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)