


OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL



Machine Id
VOLVO 26410
 Component
Diesel Engine
 Fluid
PETRO CANADA DURON SHP 10W30 (33 QTS)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

SAMPLE INFORMATION		method	limit/base	current	history1	history2
Sample Number	Client Info			PCA0094629	PCA0094588	PCA0052368
Sample Date	Client Info			01 May 2024	14 Nov 2023	26 Jan 2023
Machine Age	mls	Client Info		633775	610669	586079
Oil Age	mls	Client Info		23106	24590	36309
Oil Changed	Client Info			Changed	Changed	Changed
Sample Status				NORMAL	NORMAL	NORMAL

CONTAMINATION		method	limit/base	current	history1	history2
Fuel	WC Method	>6.0		<1.0	<1.0	<1.0
Water	WC Method	>0.2		NEG	NEG	NEG
Glycol	WC Method			NEG	NEG	NEG

WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>100	36	35	38
Chromium	ppm	ASTM D5185m	>20	1	<1	1
Nickel	ppm	ASTM D5185m	>2	1	0	<1
Titanium	ppm	ASTM D5185m		<1	0	<1
Silver	ppm	ASTM D5185m	>2	0	0	0
Aluminum	ppm	ASTM D5185m	>25	17	15	13
Lead	ppm	ASTM D5185m	>40	<1	0	1
Copper	ppm	ASTM D5185m	>330	7	4	4
Tin	ppm	ASTM D5185m	>15	1	0	1
Vanadium	ppm	ASTM D5185m		<1	0	0
Cadmium	ppm	ASTM D5185m		<1	0	0




ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	2	8	0	1
Barium	ppm	ASTM D5185m	0	2	2	0
Molybdenum	ppm	ASTM D5185m	50	71	62	60
Manganese	ppm	ASTM D5185m	0	<1	0	<1
Magnesium	ppm	ASTM D5185m	950	889	915	909
Calcium	ppm	ASTM D5185m	1050	1137	1077	1048
Phosphorus	ppm	ASTM D5185m	995	1047	943	905
Zinc	ppm	ASTM D5185m	1180	1191	1177	1216
Sulfur	ppm	ASTM D5185m	2600	2741	2396	2828

CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	9	10	11
Sodium	ppm	ASTM D5185m		8	15	13
Potassium	ppm	ASTM D5185m	>20	6	3	<1

INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844	>3	0.8	0.8	1.1
Nitration	Abs/cm	*ASTM D7624	>20	9.8	10.0	11.0
Sulfation	Abs/.1mm	*ASTM D7415	>30	22.6	23.0	23.3

FLUID DEGRADATION		method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414	>25	18.3	18.9	19.3
Base Number (BN)	mg KOH/g	ASTM D2896		5.0	4.8	5.6





OIL ANALYSIS REPORT



VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG

FLUID PROPERTIES	method	limit/base	current	history1	history2
Visc @ 100°C	cSt	ASTM D445	12.00	11.2	11.3

GRAPHS



Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : PCA0094629 **Received** : 10 May 2024
Lab Number : 06176606 **Tested** : 13 May 2024
Unique Number : 11022659 **Diagnosed** : 13 May 2024 - Wes Davis
Test Package : FLEET

PERDUE FARMS - WASHINGTON
 P.O. BOX 539
 WASHINGTON, IN
 US 47501
 Contact: DEREK RYAN
 derek.ryan@perdue.com
 T: (812)257-3023
 F:

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)