

OIL ANALYSIS REPORT




KEMP QUARRIES / BCS - GRAVETTE [69469]

WL134

Component Transmission (Manual)

PETRO CANADA PRODURO TO-4 SAE 30 (--- GAL)





DIAGNOSIS

Recommendation

Resample at the next service interval to monitor. (Customer Sample Comment: Pm2)

All component wear rates are normal.

Contamination

There is no indication of any contamination in the


Fluid Condition


The condition of the oil is acceptable for the time in service.

SAMPLE INFOR	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		PCA0108565	PCA0069858	PCA008453
Sample Date		Client Info		24 Apr 2024	09 Jan 2024	27 Jul 2023
Machine Age	hrs	Client Info		27092	26559	26117
Dil Age	hrs	Client Info		26650	442	26117
Dil Changed	1113	Client Info		Changed	N/A	Changed
Sample Status		Client inio		NORMAL	NORMAL	NORMAL
·			11 1. 1			
CONTAMINAT Vater	ION	method WC Method	limit/base >0.1	current	history1 NEG	history2 NEG
	0			NEG		
WEAR METAL	.S	method	limit/base	current	history1	history2
ron	ppm	ASTM D5185m	>200	0	2	5
Chromium	ppm	ASTM D5185m	>5	<1	<1	0
lickel	ppm		>5	0	0	0
ītanium	ppm	ASTM D5185m		0	<1	<1
Silver	ppm	ASTM D5185m		0	0	0
lluminum	ppm	ASTM D5185m	>25	0	<1	0
ead	ppm	ASTM D5185m	>45	0	2	0
Copper	ppm	ASTM D5185m	>225	5	5	7
īn	ppm	ASTM D5185m	>10	<1	1	0
/anadium	ppm	ASTM D5185m		0	<1	<1
Cadmium	ppm	ASTM D5185m		0	0	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	2	2	0	2
Barium	ppm	ASTM D5185m	0	1	0	0
Nolybdenum	ppm	ASTM D5185m	0	0	<1	3
/langanese	ppm	ASTM D5185m	9	<1	<1	0
/lagnesium	ppm	ASTM D5185m	1	19	21	29
Calcium	ppm	ASTM D5185m	3131	2954	2742	2709
Phosphorus	ppm	ASTM D5185m	1194	1007	1032	936
Zinc Zinc	ppm	ASTM D5185m	1281	1151	1174	1112
Sulfur	ppm	ASTM D5185m	3811	4572	4276	4187
CONTAMINAN	ITS	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>125	3	3	4
Sodium	ppm	ASTM D5185m		1	2	1
Potassium	ppm	ASTM D5185m	>20	0	0	0
VISUAL		method	limit/base	current	history1	history2
	scalar	*Visual	NONE	NONE	NONE	NONE
Vhite Metal			NIONIE	NONE	NONE	NONE
	scalar	*Visual	NONE	NONE	INOINE	11011
ellow Metal		*Visual *Visual	NONE	NONE	NONE	NONE
'ellow Metal Precipitate	scalar					
Yellow Metal Precipitate Silt	scalar scalar	*Visual	NONE	NONE	NONE	NONE
'ellow Metal Precipitate Silt Debris	scalar scalar scalar	*Visual *Visual	NONE NONE	NONE NONE	NONE NONE	NONE NONE
Vellow Metal Precipitate Silt Debris Sand/Dirt	scalar scalar scalar scalar	*Visual *Visual *Visual	NONE NONE	NONE NONE NONE	NONE NONE NONE	NONE NONE
Yellow Metal Precipitate Silt Debris Sand/Dirt Appearance	scalar scalar scalar scalar scalar scalar	*Visual *Visual *Visual *Visual *Visual	NONE NONE NONE NONE NORML	NONE NONE NONE NONE NORML	NONE NONE NONE NONE NORML	NONE NONE NONE NONE
White Metal Vellow Metal Precipitate Silt Debris Sand/Dirt Appearance Odor Emulsified Water	scalar scalar scalar scalar scalar	*Visual *Visual *Visual *Visual	NONE NONE NONE	NONE NONE NONE	NONE NONE NONE	NONE NONE NONE



OIL ANALYSIS REPORT







Laboratory Sample No.

: PCA0108565 Lab Number : 06177986 Unique Number : 11029312

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 13 May 2024

Tested : 14 May 2024 Diagnosed : 15 May 2024 - Sean Felton

15100 N Hwy 59 Sulphur Springs, AR

US 72768 Contact:

Test Package : MOB 1 Certificate 12367 To discuss this sample report, contact Customer Service at 1-800-237-1369.

gravette@bentoncountystone.com T:

Kemp Quarries - Benton County Stone - Gravette

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

F: