

OIL ANALYSIS REPORT

Sample Rating Trend



Machine Id

522078-SW7218 FREIGHTLINER CASCADIA 125

Diesel Engine

PETRO CANADA DURON SHP 15W40 (--- 0

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

All component wear rates are normal.

Contamination

There is no indication of any contamination in the


Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

AL)			Dec2023	Apr2024		
SAMPLE INFORI	MATION	method	limit/base	current	history1	history2
Sample Number	W// (1101)	Client Info		GFL0115322	GFL0066583	
Sample Date		Client Info		22 Apr 2024	29 Dec 2023	
Machine Age	mls	Client Info		0	0	
Dil Age	mls	Client Info		0	0	
•	11115	Client Info		N/A	N/A	
Oil Changed		Ciletit IIIIO		NORMAL	NORMAL	
Sample Status	1011					
CONTAMINAT	ION	method	limit/base	current	history1	history2
uel		WC Method	>5	<1.0	<1.0	
Vater		WC Method	>0.2	NEG	NEG	
Slycol		WC Method		NEG	NEG	
WEAR METAL	S	method	limit/base	current	history1	history2
ron	ppm	ASTM D5185m	>80	34	28	
Chromium	ppm	ASTM D5185m	>5	<1	1	
lickel	ppm	ASTM D5185m	>2	0	<1	
- itanium	ppm	ASTM D5185m		0	<1	
Silver	ppm	ASTM D5185m	>3	0	0	
Aluminum	ppm	ASTM D5185m	>30	10	3	
ead	ppm	ASTM D5185m	>30	0	<1	
Copper	ppm	ASTM D5185m	>150	7	6	
in	ppm	ASTM D5185m	>5	0	<1	
/anadium	ppm	ASTM D5185m		0	0	
Cadmium	ppm	ASTM D5185m		0	<1	
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	0	1	4	
Barium	ppm	ASTM D5185m	0	0	8	
Nolybdenum	ppm	ASTM D5185m	60	56	62	
Manganese	ppm	ASTM D5185m	0	<1	<1	
/lagnesium	ppm	ASTM D5185m	1010	763	825	
Calcium	ppm	ASTM D5185m	1070	1181	1213	
Phosphorus	ppm	ASTM D5185m	1150	940	959	
Zinc	ppm	ASTM D5185m	1270	1161	1165	
Sulfur	ppm	ASTM D5185m		3372	3386	
CONTAMINAN	TS	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>20	17	9	
Sodium	ppm	ASTM D5185m		1	0	
otassium	ppm	ASTM D5185m	>20	5	6	
INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844	>3	0.3	0.3	
Nitration	Abs/cm	*ASTM D7624	>20	7.6	6.3	
Sulfation	Abs/.1mm	*ASTM D7415	>30	19.8	19.0	
FLUID DEGRA	AOLTAC	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414	>25	15.7	14.8	
Base Number (BN)	mg KOH/g	ASTM D2896	9.8	8.8	8.6	
Jaco Namber (DN)	mg Normg	AOTIVI DE000	0.0	0.0	0.0	





OIL ANALYSIS REPORT





VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	LIGHT	NONE	
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	
Precipitate	scalar	*Visual	NONE	NONE	NONE	
Silt	scalar	*Visual	NONE	NONE	NONE	
Debris	scalar	*Visual	NONE	NONE	NONE	
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	
Appearance	scalar	*Visual	NORML	NORML	NORML	
Odor	scalar	*Visual	NORML	NORML	NORML	
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	
Free Water	scalar	*Visual		NEG	NEG	

FLUID PROPE	ERITES	metnoa	ilmit/base	current	nistory i	nistory2
Visc @ 100°C	cSt	ASTM D445	15.4	14.0	14.2	











13 12



Certificate 12367

Sample No. : GFL0115322 Lab Number : 06178252 Unique Number : 11029578

Test Package : FLEET

: WearCheck USA - 501 Madison Ave., Cary, NC 27513

To discuss this sample report, contact Customer Service at 1-800-237-1369.

Received : 13 May 2024 Tested : 14 May 2024 Diagnosed

: 14 May 2024 - Wes Davis

GFL Environmental - 980 - Northside Hauling

1820 Candle Ridge Park Dr Houston, TX

US 77073 Contact: Edwin Collins ecollins@gflenv.com

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:

F: