




OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL



Area
(RB27051)
Machine Id
924048
Component
Diesel Engine
Fluid
PETRO CANADA DURON SHP 15W40 (38 QTS)



DIAGNOSIS

Recommendation

No corrective action is recommended at this time. Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

Fuel content negligible. There is no indication of any contamination in the oil.

Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

SAMPLE INFORMATION

	method	limit/base	current	history1	history2
Sample Number	Client Info		GFL0120605	GFL0108553	GFL0066125
Sample Date	Client Info		06 May 2024	22 Mar 2024	05 Oct 2023
Machine Age	hrs	Client Info	0	4998	4567
Oil Age	hrs	Client Info	0	600	500
Oil Changed	Client Info		N/A	Changed	Changed
Sample Status			NORMAL	SEVERE	SEVERE

CONTAMINATION

	method	limit/base	current	history1	history2
Water	WC Method	>0.2	NEG	NEG	NEG
Glycol	WC Method		NEG	NEG	NEG

WEAR METALS

	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m >120	2	31	31
Chromium	ppm	ASTM D5185m >20	0	1	<1
Nickel	ppm	ASTM D5185m >5	0	<1	<1
Titanium	ppm	ASTM D5185m >2	0	<1	0
Silver	ppm	ASTM D5185m >2	0	<1	0
Aluminum	ppm	ASTM D5185m >20	<1	4	3
Lead	ppm	ASTM D5185m >40	0	1	2
Copper	ppm	ASTM D5185m >330	0	24	42
Tin	ppm	ASTM D5185m >15	0	2	3
Vanadium	ppm	ASTM D5185m	0	<1	0
Cadmium	ppm	ASTM D5185m	0	<1	0

ADDITIVES

	method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m 0	9	4	7
Barium	ppm	ASTM D5185m 0	0	0	0
Molybdenum	ppm	ASTM D5185m 60	62	56	44
Manganese	ppm	ASTM D5185m 0	0	<1	<1
Magnesium	ppm	ASTM D5185m 1010	991	848	711
Calcium	ppm	ASTM D5185m 1070	1131	995	825
Phosphorus	ppm	ASTM D5185m 1150	1055	936	766
Zinc	ppm	ASTM D5185m 1270	1227	1102	921
Sulfur	ppm	ASTM D5185m 2060	4026	2807	2108

CONTAMINANTS

	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m >25	4	6	4
Sodium	ppm	ASTM D5185m	2	2	2
Potassium	ppm	ASTM D5185m >20	0	4	2
Fuel	%	ASTM D3524 >3.0	0.2	▲ 9.2	▲ 19.6

INFRA-RED





	method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844 >4	0.1	▲ 4	3.3
Nitration	Abs/cm	*ASTM D7624 >20	4.2	10.9	10.5
Sulfation	Abs/.1mm	*ASTM D7415 >30	18.7	25.3	24.0

FLUID DEGRADATION

	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414 >25	14.1	15.3	14.5
Base Number (BN)	mg KOH/g	ASTM D2896 9.8	9.5	5.5	7.2







OIL ANALYSIS REPORT



VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG

FLUID PROPERTIES	method	limit/base	current	history1	history2
Visc @ 100°C	cSt	ASTM D445	15.4	14.7	13.2 ▲ 10.9

GRAPHS



Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : GFL0120605 **Received** : 14 May 2024
Lab Number : 06178355 **Tested** : 16 May 2024
Unique Number : 11029681 **Diagnosed** : 16 May 2024 - Wes Davis
Test Package : FLEET (Additional Tests: PercentFuel)

GFL Environmental - 904 - Chippewa Falls HC
 11888 & 11863 30th Avenue
 Chippewa Falls, WI
 US 54729
 Contact: Andy Kane

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T: (715)202-3420
F: