




OIL ANALYSIS REPORT



Machine Id
WL0187
 Component
Diesel Engine
 Fluid
MACK 15W40 (--- GAL)

Sample Rating Trend



NORMAL



DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

SAMPLE INFORMATION

	method	limit/base	current	history1	history2
Sample Number	Client Info		GFL0108503	GFL0066283	GFL0060368
Sample Date	Client Info		01 May 2024	19 Oct 2023	16 Jan 2023
Machine Age	hrs	Client Info	17268	500	500
Oil Age	hrs	Client Info	500	500	500
Oil Changed	Client Info		Not Changed	Changed	Changed
Sample Status			NORMAL	NORMAL	SEVERE

CONTAMINATION

	method	limit/base	current	history1	history2
Fuel	WC Method	>5	<1.0	1.4	▲ 16.6
Water	WC Method	>0.2	NEG	NEG	NEG
Glycol	WC Method		NEG	NEG	NEG

WEAR METALS

	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m >100	4	7	▲ 330
Chromium	ppm	ASTM D5185m >20	<1	0	4
Nickel	ppm	ASTM D5185m >2	0	0	▲ 6
Titanium	ppm	ASTM D5185m >2	0	0	0
Silver	ppm	ASTM D5185m >2	0	0	0
Aluminum	ppm	ASTM D5185m >25	<1	<1	17
Lead	ppm	ASTM D5185m >40	0	0	41
Copper	ppm	ASTM D5185m >330	9	0	94
Tin	ppm	ASTM D5185m >15	<1	0	6
Vanadium	ppm	ASTM D5185m	0	0	0
Cadmium	ppm	ASTM D5185m	0	0	0

ADDITIVES

	method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	98	6	18
Barium	ppm	ASTM D5185m	1	0	0
Molybdenum	ppm	ASTM D5185m	49	60	50
Manganese	ppm	ASTM D5185m	<1	0	3
Magnesium	ppm	ASTM D5185m	370	890	690
Calcium	ppm	ASTM D5185m	1750	1076	976
Phosphorus	ppm	ASTM D5185m	1062	973	798
Zinc	ppm	ASTM D5185m	1208	1191	937
Sulfur	ppm	ASTM D5185m	3935	2959	3003

CONTAMINANTS

	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m >25	6	4	21
Sodium	ppm	ASTM D5185m	30	4	13
Potassium	ppm	ASTM D5185m >20	2	0	6

INFRA-RED




	method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844 >3	0.1	0.5	2.8
Nitration	Abs/cm	*ASTM D7624 >20	4.6	6.8	11.8
Sulfation	Abs/.1mm	*ASTM D7415 >30	18.2	18.0	24.5

FLUID DEGRADATION

	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414 >25	13.1	14.0	18.0
Base Number (BN)	mg KOH/g	ASTM D2896	9.6	9.3	10.4







OIL ANALYSIS REPORT



VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG

FLUID PROPERTIES	method	limit/base	current	history1	history2
Visc @ 100°C	cSt	ASTM D445	14.7	14.2	▲ 8.7

GRAPHS



Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : GFL0108503 **Received** : 14 May 2024
Lab Number : 06178397 **Tested** : 14 May 2024
Unique Number : 11029723 **Diagnosed** : 14 May 2024 - Wes Davis
Test Package : FLEET

GFL Environmental - 938 - Hager City
 W9724 WIS-35
 HAGER CITY, WI
 US 54014
 Contact: ANDY KANE

To discuss this sample report, contact Customer Service at 1-800-237-1369.
 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)