

Area (71214Z) Walgreens - Tractor [Walgreens - Tractor] 136A624043

Diesel Engine

PETRO CANADA DURON SHP 10W30 (11 GAL

DIAGNOSIS

Recommendation

No corrective action is recommended at this time. Resample at the next service interval to monitor.

Wear

All component wear rates are normal.


Contamination

Elevated aluminum (AI) and/or lead (Pb) and potassium (K) levels in your metals analysis are likely a result of solder flux release into the lubricant and is common on new equipment/components. There is no indication of any contamination in the oil.

Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

GAL)				May/2024		
SAMPLE INFOR	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		PCA0105704		
Sample Date		Client Info		02 May 2024		
Machine Age	mls	Client Info		10722		
Oil Age	mls	Client Info		10722		
Oil Changed		Client Info		Not Changd		
Sample Status				NORMAL		
CONTAMINAT	ION	method	limit/base	current	history1	history2
Fuel		WC Method	>5	<1.0		
Water		WC Method	>0.2	NEG		
Glycol		WC Method		NEG		
WEAR METAL	S	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>80	30		
Chromium	ppm	ASTM D5185m	>5	2		
Nickel	ppm	ASTM D5185m	>2	0		
Titanium	ppm	ASTM D5185m		0		
Silver	ppm	ASTM D5185m	>3	1		
Aluminum	ppm	ASTM D5185m	>30	21		
Lead	ppm	ASTM D5185m	>30	0		
Copper	ppm	ASTM D5185m	>150	116		
Tin	ppm	ASTM D5185m	>5	8		
Vanadium	ppm	ASTM D5185m		0		
Cadmium	ppm	ASTM D5185m		0		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	2	53		
Barium	ppm		0	2		
Molybdenum	ppm	ASTM D5185m	50	42		
Manganese	ppm	ASTM D5185m		4		
Magnesium	ppm	ASTM D5185m	950	538		
Calcium	ppm	ASTM D5185m	1050	1717		
Phosphorus	ppm	ASTM D5185m	995	839		
Zinc Sulfur	ppm ppm	ASTM D5185m ASTM D5185m		963 2683		
CONTAMINAN		method	limit/base	current	history1	history2
Silicon		ASTM D5185m	>20	6		nistoryz
Sodium	ppm ppm	ASTM D5185m	>20	5		
Potassium	ppm	ASTM D5185m	>20	56		
INFRA-RED	pp	method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844		0.2		TIIStory2
Nitration	% Abs/cm	*ASTM D7844		0.2 7.1		
Sulfation	Abs/cm Abs/.1mm	*ASTM D7624		23.0		
FLUID DEGRA						
			limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414	>25	20.7		
Base Number (BN)	mg KOH/g	ASTM D2896		9.0		



Sample Rating Trend





Base

15 14


13 cSt (100°C) B


May2/24 .

Viscosity @ 100°C

OIL ANALYSIS REPORT

VISUAL





To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Report Id: TSV1374 [WUSCAR] 06178451 (Generated: 05/16/2024 12:06:45) Rev: 1

Certificate 12367

Contact/Location: Paul Santanella - TSV1374

T: (860)687-1037

F: (860)687-1476