

OIL ANALYSIS REPORT





PETRO CANADA DURON SHP 10W30 (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor. Please specify the component make and model with your next sample.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.


Fluid Condition


The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

SAMPLE INFOR	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		PCA0119250		
Sample Date		Client Info		28 Feb 2024		
Machine Age	mls	Client Info		169699		
Oil Age	mls	Client Info		0		
Oil Changed		Client Info		Changed		
Sample Status				NORMAL		
CONTAMINAT	ION	method	limit/base	current	history1	history2
Fuel		WC Method	>5	<1.0		
Water		WC Method	>0.2	NEG		
Glycol		WC Method		NEG		
WEAR METAL	S	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>100	12		
Chromium	ppm	ASTM D5185m	>20	<1		
Nickel	ppm	ASTM D5185m	>4	0		
Titanium	ppm	ASTM D5185m		0		
Silver	ppm	ASTM D5185m	>3	<1		
Aluminum	ppm	ASTM D5185m	>20	3		
Lead	ppm	ASTM D5185m	>40	<1		
Copper	ppm	ASTM D5185m	>330	1		
Tin	ppm	ASTM D5185m	>15	<1		
Vanadium	ppm	ASTM D5185m		<1		
Cadmium	ppm	ASTM D5185m		0		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	2	<1		
Barium	ppm	ASTM D5185m	0	0		
Molybdenum	ppm	ASTM D5185m	50	66		
Manganese	ppm	ASTM D5185m	0	<1		
Magnesium	ppm	ASTM D5185m	950	1012		
Calcium	ppm	ASTM D5185m	1050	1324		
Phosphorus	ppm	ASTM D5185m	995	1120		
Zinc	ppm	ASTM D5185m	1180	1342		
Sulfur	ppm	ASTM D5185m	2600	3803		
CONTAMINAN	ITS	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	3		
Sodium	ppm	ASTM D5185m		<1		
Potassium	ppm	ASTM D5185m	>20	0		
INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844	>3	0.8		
Nitration	Abs/cm	*ASTM D7624	>20	10.0		
Sulfation	Abs/.1mm	*ASTM D7415	>30	20.0		
FLUID DEGRA	DATION	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414	>25	16.8		
Oxidation Base Number (BN)	Abs/.1mm mg KOH/g	*ASTM D7414 ASTM D2896	>25	16.8 8.5		




OIL ANALYSIS REPORT







VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE		
Yellow Metal	scalar	*Visual	NONE	NONE		
Precipitate	scalar	*Visual	NONE	NONE		
Silt	scalar	*Visual	NONE	NONE		
Debris	scalar	*Visual	NONE	NONE		
Sand/Dirt	scalar	*Visual	NONE	NONE		
Appearance	scalar	*Visual	NORML	NORML		
Odor	scalar	*Visual	NORML	NORML		
Emulsified Water	scalar	*Visual	>0.2	NEG		
Free Water	scalar	*Visual		NEG		
FLUID PROPE	RTIES	method	limit/base	current	history1	history2
Visc @ 100°C	cSt	ASTM D445	12.00	11.5		
GRAPHS						
Iron (ppm)				Lead (ppm)		
Savere			100-	Severe		
Severe			80	- 0		
- Abnormal			60·	Abnormal		
Abnormal			² 40	- dbnormal		
)+			20			
54			-0	24		
Feb 28/24			Feb28/24	Feb28/24		
 Aluminum (ppm)			LL.	Chromium (p	nm)	
			50-		p,	
Severe			40	Severe		
•			е ³⁰			
Abnormal			E 20-	- Abnormal		
)-			10-			
4				4		
Feb 28/24			Feb28/24	Feb 28/24		
			E.			
Copper (ppm)			80-	Silicon (ppm)		
Abnonnal						
)+			60.			
)			툡 40	Abaaaaal		
			20	Abnormal		
Feb28/24			Feb28/24 .	Feb28/24 -		
ੇ Viscosity @ 100°C			Feb	语 Base Number		
Abnormal			(0H0 K 8.0) Bu back for the second se			
Base			டு 6.0- த			
			-9 4.0-			
			age 2.0			
54			0.0	24		
Feb 28/24			Feb28/24	Feb 28/24		
LL_			LL	LL_		



Report Id: MILJER [WUSCAR] 06188292 (Generated: 05/24/2024 13:54:53) Rev: 1

Contact/Location: BILL CUCCIA - MILJER Page 2 of 2