




OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL



Machine Id
10742C AUTOCAR ACX

Component
Natural Gas Engine

Fluid
PETRO CANADA DURON GEO LD 15W40 (28 QTS)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

SAMPLE INFORMATION

method	limit/base	current	history1	history2
Sample Number	Client Info	GFL0117494	GFL0103211	GFL0089268
Sample Date	Client Info	18 May 2024	20 Dec 2023	27 Jul 2023
Machine Age	hrs	9310	8131	6963
Oil Age	hrs	0	0	0
Oil Changed	Client Info	Not Changed	Changed	Not Changed
Sample Status		NORMAL	NORMAL	NORMAL

CONTAMINATION

method	limit/base	current	history1	history2
Water	WC Method >0.1	NEG	NEG	NEG

WEAR METALS

method	limit/base	current	history1	history2
Iron	ppm ASTM D5185m >50	16	21	18
Chromium	ppm ASTM D5185m >4	2	3	2
Nickel	ppm ASTM D5185m >2	<1	<1	<1
Titanium	ppm ASTM D5185m	<1	0	0
Silver	ppm ASTM D5185m >3	<1	0	0
Aluminum	ppm ASTM D5185m >9	1	2	4
Lead	ppm ASTM D5185m >30	3	5	4
Copper	ppm ASTM D5185m >35	1	<1	0
Tin	ppm ASTM D5185m >4	<1	1	<1
Vanadium	ppm ASTM D5185m	0	<1	0
Cadmium	ppm ASTM D5185m	0	<1	0

ADDITIVES

method	limit/base	current	history1	history2
Boron	ppm ASTM D5185m 50	10	11	11
Barium	ppm ASTM D5185m 5	0	0	0
Molybdenum	ppm ASTM D5185m 50	57	64	62
Manganese	ppm ASTM D5185m 0	<1	<1	<1
Magnesium	ppm ASTM D5185m 560	607	710	678
Calcium	ppm ASTM D5185m 1510	1640	1858	1896
Phosphorus	ppm ASTM D5185m 780	779	951	861
Zinc	ppm ASTM D5185m 870	1059	1208	1108
Sulfur	ppm ASTM D5185m 2040	2879	2891	3137

CONTAMINANTS

method	limit/base	current	history1	history2
Silicon	ppm ASTM D5185m >+100	12	5	7
Sodium	ppm ASTM D5185m	5	8	9
Potassium	ppm ASTM D5185m >20	3	<1	0

INFRA-RED




method	limit/base	current	history1	history2
Soot %	% *ASTM D7844	0.1	0	0.1
Nitration	Abs/cm *ASTM D7624 >20	11.3	12.6	11.7
Sulfation	Abs/.1mm *ASTM D7415 >30	23.4	26.7	25.0

FLUID DEGRADATION

method	limit/base	current	history1	history2
Oxidation	Abs/.1mm *ASTM D7414 >25	19.3	21.9	20.6
Base Number (BN)	mg KOH/g ASTM D2896 10.2	4.0	3.9	4.3







OIL ANALYSIS REPORT



VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	LIGHT
Yellow Metal	scalar	*Visual	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	LIGHT	LIGHT
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.1	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG

FLUID PROPERTIES	method	limit/base	current	history1	history2	
Visc @ 100°C	cSt	ASTM D445	15.1	14.8	15.2	14.9

GRAPHS



Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : GFL0117494 **Received** : 23 May 2024
Lab Number : 06188631 **Tested** : 24 May 2024
Unique Number : 11045383 **Diagnosed** : 24 May 2024 - Wes Davis
Test Package : FLEET

GFL Environmental - 001 - Raleigh(CNG)
 3741 Conquest Drive
 Garner, NC
 US 27529
 Contact: Craig Johnson
 craig.johnson@gflenv.com
 T: (919)662-7100
 F: (919)662-7130

To discuss this sample report, contact Customer Service at 1-800-237-1369.
 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)