OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL

Area
KEMP QUARRIES / KEMP STONE - FAIRLAND [68773]
Machine Id
OHT042
Component
Rear Differential
Fluid
PETRO CANADA PRODURO TO-4 SAE 50 (--- GAL)

DIAGNOSIS

Recommendation
Resample at the next service interval to monitor. (Customer Sample Comment: PM-4 changed fluid)

Wear
All component wear rates are normal.

Contamination
There is no indication of any contamination in the oil.

Fluid Condition
The condition of the oil is acceptable for the time in service.

SAMPLE INFORMATION		method	limit/base	current	history1	history2
Sample Number		Client Info		**PCA0108699**	PCA0037557	PCA0025435
Sample Date		Client Info		**15 May 2024**	21 Apr 2022	24 Jan 2022
Machine Age	hrs	Client Info		**26970**	26463	25066
Oil Age	hrs	Client Info		**26970**	26463	25066
Oil Changed		Client Info		**Changed**	N/A	Changed
Sample Status				**NORMAL**	NORMAL	NORMAL

CONTAMINATION		method	limit/base	current	history1	history2
Water		WC Method	>.2	**NEG**	NEG	NEG

WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>500	**82**	147	148
Chromium	ppm	ASTM D5185m	>3	**<1**	3	3
Nickel	ppm	ASTM D5185m	>3	**<1**	1	0
Titanium	ppm	ASTM D5185m	>2	**<1**	<1	<1
Silver	ppm	ASTM D5185m	>2	**<1**	0	<1
Aluminum	ppm	ASTM D5185m	>30	**3**	7	9
Lead	ppm	ASTM D5185m	>13	**<1**	6	2
Copper	ppm	ASTM D5185m	>103	**27**	84	71
Tin	ppm	ASTM D5185m	>5	**<1**	<1	<1
Antimony	ppm	ASTM D5185m	>5	**---**	---	0
Vanadium	ppm	ASTM D5185m		**<1**	0	0
Cadmium	ppm	ASTM D5185m		**0**	0	0

ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	2	**2**	6	5
Barium	ppm	ASTM D5185m	0	**0**	0	0
Molybdenum	ppm	ASTM D5185m	0	**2**	2	2
Manganese	ppm	ASTM D5185m	0	**1**	3	2
Magnesium	ppm	ASTM D5185m	9	**29**	24	18
Calcium	ppm	ASTM D5185m	3114	**2973**	2840	3166
Phosphorus	ppm	ASTM D5185m	1099	**1005**	1015	1085
Zinc	ppm	ASTM D5185m	1245	**1218**	1144	1209
Sulfur	ppm	ASTM D5185m	7086	**6790**	7481	8363

CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>100	**38**	22	26
Sodium	ppm	ASTM D5185m		**<1**	8	4
Potassium	ppm	ASTM D5185m	>20	**4**	6	10

VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	**NONE**	LIGHT	MODER
Yellow Metal	scalar	*Visual	NONE	**NONE**	NONE	NONE
Precipitate	scalar	*Visual	NONE	**NONE**	NONE	NONE
Silt	scalar	*Visual	NONE	**NONE**	NONE	NONE
Debris	scalar	*Visual	NONE	**NONE**	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	**NONE**	NONE	NONE
Appearance	scalar	*Visual	NORML	**NORML**	NORML	NORML
Odor	scalar	*Visual	NORML	**NORML**	NORML	NORML
Emulsified Water	scalar	*Visual	>.2	**NEG**	NEG	NEG
Free Water	scalar	*Visual		**NEG**	NEG	NEG

OIL ANALYSIS REPORT



FLUID PROPERTIES		method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	213.9	**188**	194	195

SAMPLE IMAGES	method	limit/base	current	history1	history2
Color			*no image*	*no image*	*no image*
Bottom			*no image*	*no image*	*no image*

GRAPHS

















Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : PCA0108699
Lab Number : 06189822
Unique Number : 11046574
Test Package : MOB 1

Received : 23 May 2024
Tested : 30 May 2024
Diagnosed : 30 May 2024 - Angela Borella

Kemp Quarries - Kemp Stone - Fairland
18350 S 590 Rd
Fairland, OK
US 74343
Contact:
fairland@kempstone.com
T:
F:

To discuss this sample report, contact Customer Service at 1-800-237-1369.
** - Denotes test methods that are outside of the ISO 17025 scope of accreditation.*
Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)