

# **OIL ANALYSIS REPORT**









### DIAGNOSIS

### Recommendation

Resample at the next service interval to monitor.

#### Wear

All component wear rates are normal.

### Contamination

There is no indication of any contamination in the oil.


### **Fluid Condition**


The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.


SAMPLE INFOR	RMATION	method				history2
Sample Number		Client Info		GFL0115057	GFL0106701	GFL0097676
Sample Date		Client Info		16 May 2024	12 Feb 2024	19 Nov 2023
Machine Age	hrs	Client Info		24025	23385	22770
Oil Age	hrs	Client Info		640	615	285
Oil Changed		Client Info		Changed	Changed	Changed
Sample Status				NORMAL	NORMAL	NORMAL
CONTAMINA	TION	method	limit/base	current	history1	history2
Fuel		WC Method	>3.0	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
WEAR META	LS	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>90	11	18	11
Chromium	ppm	ASTM D5185m	>20	<1	1	<1
Nickel	ppm	ASTM D5185m	>2	<1	<1	0
Titanium	ppm	ASTM D5185m	>2	0	<1	0
Silver	ppm	ASTM D5185m	>2	<1	0	0
Aluminum	ppm	ASTM D5185m	>20	2	3	<1
Lead	ppm	ASTM D5185m	>40	3	<1	0
Copper	ppm	ASTM D5185m	>330	<1	11	6
Tin	ppm	ASTM D5185m	>15	<1	0	0
Vanadium	ppm	ASTM D5185m		0	<1	<1
Cadmium	ppm	ASTM D5185m		0	0	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	0	3	<1	4
Barium	ppm	ASTM D5185m	0	0	0	0
Molybdenum	ppm	ASTM D5185m	60	59	59	55
Manganese	ppm	ASTM D5185m	0	<1	0	<1
Magnesium	ppm	ASTM D5185m	1010	994	990	842
Calcium	ppm	ASTM D5185m	1070	1067	1060	1039
Phosphorus	ppm	ASTM D5185m	1150	1033	1064	998
Zinc	ppm	ASTM D5185m	1270	1327	1296	1163
Sulfur	ppm	ASTM D5185m	2060	3447	3148	2901
CONTAMINA	NTS	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	5	6	5
Sodium	ppm	ASTM D5185m		2	7	7
Potassium	ppm	ASTM D5185m	>20	<1	<1	0
INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844	>6	0.2	0.6	0.4
Nitration	Abs/cm	*ASTM D7624	>20	10.8	9.1	6.5
Sulfation	Abs/.1mm	*ASTM D7415	>30	21.8	18.8	18.3
FLUID DEGRA	DATION	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414	>25	21.8	15.4	13.9
Base Number (BN)	mg KOH/g	ASTM D2896	9.8	8.0	7.9	8.4



## **OIL ANALYSIS REPORT**









VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
<b>Emulsified Water</b>	scalar	*Visual	>0.2	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG


FLUID PROPI	ERTIES	method				history2
Visc @ 100°C	cSt	ASTM D445	15.4	14.2	13.0	12.9


### **GRAPHS**















Certificate 12367

Report Id: GFL405 [WUSCAR] 06190221 (Generated: 05/28/2024 09:07:55) Rev: 1

Laboratory Sample No.

Lab Number : 06190221 Unique Number : 11046973

Test Package : FLEET

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 : GFL0115057 Received : 24 May 2024

**Tested** : 28 May 2024 Diagnosed : 28 May 2024 - Wes Davis

GFL Environmental - 405 - Arbor Hills

7811 Chubb Rd NORTHVILLE, MI US 48168 Contact: John Nahal jnahal@gflenv.com

To discuss this sample report, contact Customer Service at 1-800-237-1369. \* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Submitted By: John Nahal

T:

F: