


OIL ANALYSIS REPORT

Sample Rating Trend





196

Machine Id

Diesel Engine

PETRO CANADA DURON SHP 10W30 (--- G

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor. Please specify the component make and model with your next sample.

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.


Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

QTS)			Sep.2023	May2024		
SAMPLE INFORI	MATION	method	limit/base	current	history1	history2
Sample Number	vii (1101)	Client Info		PCA0124605	PCA0099824	
Sample Date		Client Info		03 May 2024	14 Sep 2023	
Machine Age	mls	Client Info		281841	251274	
Oil Age	mls	Client Info		10000	10274	
Oil Changed	11113	Client Info		Changed	Changed	
Sample Status				NORMAL	NORMAL	
CONTAMINAT	ION	method	limit/base	current	history1	history2
Fuel		WC Method	>5	<1.0	<1.0	
Water		WC Method	>0.2	NEG	NEG	
Glycol		WC Method		NEG	NEG	
WEAR METAL	S	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>100	15	16	
Chromium	ppm	ASTM D5185m	>20	<1	0	
Nickel	ppm	ASTM D5185m	>4	0	0	
Titanium	ppm	ASTM D5185m		0	0	
Silver	ppm	ASTM D5185m	>3	0	0	
Aluminum	ppm	ASTM D5185m	>20	2	<1	
Lead	ppm	ASTM D5185m	>40	1	2	
Copper	ppm	ASTM D5185m	>330	<1	<1	
Tin	ppm	ASTM D5185m	>15	0	0	
Vanadium	ppm	ASTM D5185m		<1	0	
Cadmium	ppm	ASTM D5185m		0	0	
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	2	0	12	
Barium	ppm	ASTM D5185m	0	0	0	
Molybdenum	ppm	ASTM D5185m	50	63	61	
Manganese	ppm	ASTM D5185m	0	<1	0	
Magnesium	ppm	ASTM D5185m	950	1043	1061	
Calcium	ppm	ASTM D5185m	1050	1229	1226	
Phosphorus	ppm	ASTM D5185m	995	1127	1106	
Zinc	ppm	ASTM D5185m	1180	1329	1389	
Sulfur	ppm	ASTM D5185m	2600	3709	3487	
CONTAMINAN	TS	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	4	4	
Sodium	ppm	ASTM D5185m		2	2	
Potassium	ppm	ASTM D5185m	>20	2	7	
INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844	>3	0.4	0.4	
Nitration	Abs/cm	*ASTM D7624	>20	8.3	8.6	
Sulfation	Abs/.1mm	*ASTM D7415	>30	19.8	20.5	
FLUID DEGRA	DATION	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414	>25	15.9	16.2	
Base Number (BN)	mg KOH/g	ASTM D2896		7.7	7.7	




OIL ANALYSIS REPORT




VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	
Precipitate	scalar	*Visual	NONE	NONE	NONE	
Silt	scalar	*Visual	NONE	NONE	NONE	
Debris	scalar	*Visual	NONE	NONE	NONE	
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	
Appearance	scalar	*Visual	NORML	NORML	NORML	
Odor	scalar	*Visual	NORML	NORML	NORML	
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	
Free Water	scalar	*Visual		NEG	NEG	


L LOID PROPE	ERITES	method			riistory i	HISTORYZ
Visc @ 100°C	cSt	ASTM D445	12.00	11.3	11.2	

GRAPHS



10	copper	
8-	nennennennen lead	
6-		
4-		
2-	264.43464.45.200mm=000.mm=00.mm=	
0-	22	24
	Sep14/23	May3/24
	Viscosity @ 100°C	









Certificate 12367

Laboratory Sample No.

: PCA0124605 Lab Number : 06193553 Unique Number : 11050305

Test Package : FLEET

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 29 May 2024 Tested

: 30 May 2024 Diagnosed : 30 May 2024 - Wes Davis **GAS FIELD SPECIALISTS** 114 PA-660

MANSFIELD, PA US 16933

Contact: TARA MUIRHEAD tara.muirhead@gfsinc.net T:

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

To discuss this sample report, contact Customer Service at 1-800-237-1369.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

F: