OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL

Machine Id
934035
Component
Natural Gas Engine
Fluid
{not provided} (--- GAL)

DIAGNOSIS

Recommendation
Resample at the next service interval to monitor. Please specify the brand, type, and viscosity of the oil on your next sample.

Wear
Metal levels are typical for a new component breaking in.

Contamination
There is no indication of any contamination in the oil.

Fluid Condition
The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

SAMPLE INFORMATION		method	limit/base	current	history1	history2
Sample Number		Client Info		**GFL0122053**	GFL0116604	GFL0111887
Sample Date		Client Info		**24 May 2024**	02 May 2024	12 Mar 2024
Machine Age	hrs	Client Info		**1054**	901	719
Oil Age	hrs	Client Info		**1054**	901	719
Oil Changed		Client Info		**Not Changd**	Not Changd	Not Changd
Sample Status				**NORMAL**	NORMAL	NORMAL

CONTAMINATION		method	limit/base	current	history1	history2
Water		WC Method	>0.1	**NEG**	NEG	NEG

WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>50	**71**	81	62
Chromium	ppm	ASTM D5185m	>4	**2**	2	2
Nickel	ppm	ASTM D5185m	>2	**2**	1	<1
Titanium	ppm	ASTM D5185m		**<1**	0	0
Silver	ppm	ASTM D5185m	>3	**<1**	0	<1
Aluminum	ppm	ASTM D5185m	>9	**18**	20	15
Lead	ppm	ASTM D5185m	>30	**2**	<1	2
Copper	ppm	ASTM D5185m	>35	**15**	18	16
Tin	ppm	ASTM D5185m	>4	**2**	2	2
Antimony	ppm	ASTM D5185m		**---**	---	---
Vanadium	ppm	ASTM D5185m		**0**	0	0
Cadmium	ppm	ASTM D5185m		**0**	0	0

ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		**7**	10	7
Barium	ppm	ASTM D5185m		**3**	<1	2
Molybdenum	ppm	ASTM D5185m		**56**	65	56
Manganese	ppm	ASTM D5185m		**11**	13	11
Magnesium	ppm	ASTM D5185m		**740**	833	758
Calcium	ppm	ASTM D5185m		**1316**	1399	1188
Phosphorus	ppm	ASTM D5185m		**814**	845	747
Zinc	ppm	ASTM D5185m		**983**	1051	944
Sulfur	ppm	ASTM D5185m		**2565**	2733	2523

CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>+100	**22**	27	27
Sodium	ppm	ASTM D5185m		**7**	7	4
Potassium	ppm	ASTM D5185m	>20	**17**	17	14

INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844		**0**	0	0
Nitration	Abs/cm	*ASTM D7624	>20	**12.7**	12.6	12.1
Sulfation	Abs/.1mm	*ASTM D7415	>30	**26.3**	26.3	25.2

FLUID DEGRADATION		method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414	>25	**23.5**	23.5	23.3
Base Number (BN)	mg KOH/g	ASTM D2896		**3.5**	3.1	3.0

OIL ANALYSIS REPORT

FT-IR (Direct Trend)



Base Number



Viscosity @ 100°C



VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	**NONE**	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	**NONE**	NONE	NONE
Precipitate	scalar	*Visual	NONE	**NONE**	NONE	NONE
Silt	scalar	*Visual	NONE	**NONE**	NONE	NONE
Debris	scalar	*Visual	NONE	**NONE**	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	**NONE**	NONE	NONE
Appearance	scalar	*Visual	NORML	**NORML**	NORML	NORML
Odor	scalar	*Visual	NORML	**NORML**	NORML	NORML
Emulsified Water	scalar	*Visual	>0.1	**NEG**	NEG	NEG
Free Water	scalar	*Visual		**NEG**	NEG	NEG

FLUID PROPERTIES		method	limit/base	current	history1	history2
Visc @ 100°C	cSt	ASTM D445		**14.7**	14.6	14.5

GRAPHS

Ferrous Alloys



Non-ferrous Metals



Viscosity @ 100°C



Base Number



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : GFL0122053
Lab Number : 06193836
Unique Number : 11055959
Test Package : FLEET

Received : 29 May 2024
Tested : 30 May 2024
Diagnosed : 31 May 2024 - Angela Borella

To discuss this sample report, contact Customer Service at 1-800-237-1369.
** - Denotes test methods that are outside of the ISO 17025 scope of accreditation.*
Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

GFL Environmental - 652 - Fredericksburg Hauling
10954 Houser Drive
Fredericksburg, VA
US 22408
Contact: WILLIAM MILO
wmilo@gflenv.com
T:
F: