


OIL ANALYSIS REPORT

(14253Z) Walgreens - Tractor [Walgreens - Tractor] 136A61440

Diesel Engine

PETRO CANADA DURON SHP 10W30 (11 GAL)





DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

All component wear rates are normal.

Contamination

There is no indication of any contamination in the


Fluid Condition


The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.


une,									
SAMPLE INFORI	MATION	method	limit/base	current	history1	history2			
Sample Number		Client Info		PCA0128201	PCA0116415	PCA0097097			
Sample Date		Client Info		22 May 2024	26 Jan 2024	05 Jun 2023			
Machine Age	mls	Client Info		299593	285670	252538			
Oil Age	mls	Client Info		13923	33135	45852			
Oil Changed		Client Info		Not Changd	Changed	Changed			
Sample Status				NORMAL	NORMAL	NORMAL			
CONTAMINAT	ION	method	limit/base	current	history1	history2			
Fuel		WC Method	>2.0	<1.0	<1.0	<1.0			
Water		WC Method	>0.2	NEG	NEG	NEG			
Glycol		WC Method		NEG	NEG	NEG			
WEAR METAL	S	method	limit/base	current	history1	history2			
Iron	ppm	ASTM D5185m	>100	17	29	40			
Chromium	ppm	ASTM D5185m	>20	1	2	2			
Nickel	ppm	ASTM D5185m	>4	0	0	<1			
Titanium	ppm	ASTM D5185m		<1	<1	0			
Silver	ppm	ASTM D5185m	>3	<1	0	0			
Aluminum	ppm	ASTM D5185m	>20	3	5	4			
Lead	ppm	ASTM D5185m	>40	2	3	2			
Copper	ppm	ASTM D5185m	>330	4	1	6			
Tin	ppm	ASTM D5185m	>15	1	1	<1			
Vanadium	ppm	ASTM D5185m		<1	0	0			
Cadmium	ppm	ASTM D5185m		<1	0	0			
ADDITIVES		method	limit/base	current	history1	history2			
Boron	ppm	ASTM D5185m	2	4	12	7			
Barium	ppm	ASTM D5185m	0	<1	<1	0			
Molybdenum	ppm	ASTM D5185m	50	65	60	70			
Manganese	ppm	ASTM D5185m	0	<1	<1	<1			
Magnesium	ppm	ASTM D5185m	950	997	791	991			
Calcium	ppm	ASTM D5185m	1050	1249	1106	1221			
Phosphorus	ppm	ASTM D5185m	995	1152	987	1092			
Zinc	ppm	ASTM D5185m	1180	1343	1096	1382			
Sulfur	ppm	ASTM D5185m	2600	3819	2755	3646			
CONTAMINANTS method limit/base current history1 history2									
Silicon	ppm	ASTM D5185m	>25	4	5	7			
Sodium	ppm	ASTM D5185m		2	4	2			
Potassium	ppm	ASTM D5185m	>20	7	10	8			
INFRA-RED		method	limit/base	current	history1	history2			
Soot %	%	*ASTM D7844	>3	0.3	0.5	0.5			
Nitration	Abs/cm	*ASTM D7624	>20	8.3	11.0	11.2			
Sulfation	Abs/.1mm	*ASTM D7415	>30	19.5	25.2	24.4			
FLUID DEGRADATION method limit/base current history1 history2									
Oxidation	Abs/.1mm	*ASTM D7414	>25	15.9	23.1	21.7			
Base Number (BN)	mg KOH/g	ASTM D2896	/20	7.8	5.9	5.2			
Dase Number (DIV)	my KON/g	AOTIVI DZ030		7.0	0.0	J. Z			




OIL ANALYSIS REPORT













FLUID	PROPERTIES	method			history1	history2
Visc @ 100	°C cSt	ASTM D445	12.00	11.1	10.9	11.0

GRAPHS













Laboratory Sample No.

: PCA0128201 Lab Number : 06195059 Unique Number : 11057182

: WearCheck USA - 501 Madison Ave., Cary, NC 27513

Received **Tested** Diagnosed

: 30 May 2024 : 31 May 2024 : 31 May 2024 - Wes Davis

Transervice - Shop 1373 - Berkeley-Anderson/Pendergrass 101 Alliance Parkway Willamston, SC

US 29697 Contact: Sonny Boucher

Test Package : FLEET Certificate 12367 To discuss this sample report, contact Customer Service at 1-800-237-1369.

T: (864)226-2304

sboucher@transervice.com

 st - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

F: (864)226-2329 Submitted By: Sonny Boucher