


OIL ANALYSIS REPORT

(89622X) Walgreens - Tractor [Walgreens - Tractor] 136A68010

Diesel Engine

PETRO CANADA DURON SHP 10W30 (11 GAL)





DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

All component wear rates are normal.

Contamination

There is no indication of any contamination in the


Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

une)						
SAMPLE INFORI	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		PCA0123055	PCA0110520	PCA0093498
Sample Date		Client Info		16 May 2024	05 Dec 2023	17 Jul 2023
Machine Age	mls	Client Info		198820	178096	178096
Oil Age	mls	Client Info		198820	178096	178096
Oil Changed		Client Info		Changed	Changed	Changed
Sample Status				NORMAL	NORMAL	NORMAL
CONTAMINAT	ION	method	limit/base	current	history1	history2
Fuel		WC Method	>5	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
WEAR METAL	S	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>80	24	30	28
Chromium	ppm	ASTM D5185m	>5	<1	<1	<1
Nickel	ppm	ASTM D5185m	>2	0	<1	0
Titanium	ppm	ASTM D5185m		22	6	3
Silver	ppm	ASTM D5185m	>3	<1	<1	0
Aluminum	ppm	ASTM D5185m	>30	5	4	4
Lead	ppm	ASTM D5185m	>30	<1	0	0
Copper	ppm	ASTM D5185m	>150	6	3	3
Tin	ppm	ASTM D5185m	>5	<1	<1	<1
Vanadium	ppm	ASTM D5185m		<1	<1	<1
Cadmium	ppm	ASTM D5185m		<1	0	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	2	20	9	4
Barium	ppm	ASTM D5185m	0	0	0	0
Molybdenum	ppm	ASTM D5185m	50	44	51	54
Manganese	ppm	ASTM D5185m	0	<1	<1	<1
Magnesium	ppm	ASTM D5185m	950	793	802	883
Calcium	ppm	ASTM D5185m	1050	1469	1080	1265
Phosphorus	ppm	ASTM D5185m	995	1024	872	954
Zinc	ppm	ASTM D5185m	1180	1242	1105	1249
Sulfur	ppm	ASTM D5185m	2600	3720	2682	3507
CONTAMINAN	TS	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>20	10	8	7
Sodium	ppm	ASTM D5185m		2	2	3
Potassium	ppm	ASTM D5185m	>20	4	3	4
INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844	>3	0.5	0.7	0.6
Nitration	Abs/cm	*ASTM D7624	>20	10.5	11.2	10.9
Sulfation	Abs/.1mm	*ASTM D7415	>30	22.0	23.3	22.2
FLUID DEGRADATION method limit/base current history1 history2						
Oxidation	Abs/.1mm	*ASTM D7414	>25	18.8	20.2	18.8
Base Number (BN)	mg KOH/g	ASTM D2896		6.1	5.4	6.3
()	0 - 9					




OIL ANALYSIS REPORT





VISUAL		method	limit/base	current	history1	history2
VIOO/IL		111011100	mme bacc	Janoni	111010171	111010172
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG


FLUID PROPI	ERHES	method				history2
Visc @ 100°C	cSt	ASTM D445	12.00	11.5	10.8	11.4

GRAPHS













Certificate 12367

Laboratory Sample No.

: PCA0123055 Lab Number : 06195064 Unique Number : 11057187 Test Package : FLEET

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 30 May 2024 **Tested**

: 31 May 2024 Diagnosed : 31 May 2024 - Wes Davis

Transervice - Shop 1376 - Berkeley-Linden 3425 Tremley Point Road Linden, NJ US 07036

Contact: Shop 1376 Oil Analysis shop1376@transervice.com

To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:

F: