

## **OIL ANALYSIS REPORT**



#### Machine Id **T325** Component **Rear Differential** Fluid **CHEVRON RPM SYNTHETIC GEAR 75W90 (12 QTS)**

### DIAGNOSIS

#### Recommendation

Resample at the next service interval to monitor.

#### Wear

All component wear rates are normal.

#### Contamination

There is no indication of any contamination in the oil.


#### Fluid Condition

The condition of the oil is acceptable for the time in service.

SAMPLE INFOR	RMATION	method	limit/base	current	history1	history2
Sample Number		Client Info		PCA0120595		
Sample Date		Client Info		10 May 2024		
Machine Age	hrs	Client Info		44549		
Oil Age	hrs	Client Info		44549		
Oil Changed		Client Info		Not Changd		
Sample Status				NORMAL		
CONTAMINAT		method	limit/base	current	history1	history2
Water		WC Method		NEG		
WEAR METAL	S	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>500	241		
Chromium	ppm	ASTM D5185m	>10	1		
Nickel	ppm		>10	0		
Titanium	ppm	ASTM D5185m		0		
Silver	ppm	ASTM D5185m		0		
Aluminum	ppm	ASTM D5185m	>25	<1		
Lead	ppm	ASTM D5185m	>25	0		
Copper	ppm	ASTM D5185m	>100	1		
Tin	ppm		>100	، <1		
Vanadium	ppm	ASTM D5185m	>10	<1		
Cadmium	ppm	ASTM D5185m		<1		
	ррш					
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		72		
Barium	ppm	ASTM D5185m		5		
Molybdenum	ppm	ASTM D5185m		<1		
Manganese	ppm	ASTM D5185m		5		
Magnesium	ppm	ASTM D5185m		192		
Calcium	ppm	ASTM D5185m		9		
Phosphorus	ppm	ASTM D5185m		1795		
Zinc	ppm	ASTM D5185m		18		
Sulfur	ppm	ASTM D5185m		30013		
CONTAMINAN	NTS	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>75	16		
Sodium	ppm	ASTM D5185m		6		
Potassium	ppm	ASTM D5185m	>20	2		
VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE		
Yellow Metal	scalar	*Visual	NONE	NONE		
Precipitate	scalar	*Visual	NONE	NONE		
Silt	scalar	*Visual	NONE	NONE		
Debris	scalar	*Visual	NONE	LIGHT		
Sand/Dirt	scalar	*Visual	NONE	NONE		
Appearance	scalar	*Visual	NORML	NORML		
Odor	scalar	*Visual	NORML	NORML		
Emulsified Water	scalar	*Visual	>.2	NEG		
Emulsified Water Free Water	scalar scalar	*Visual *Visual		NEG		 E - Matt Quinlan



# **OIL ANALYSIS REPORT**



FLUID PROPI	ERTIES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	110	98.2		
SAMPLE IMA	GES	method	limit/base	current	history1	history2
Color				no image	no image	no image
Bottom				no image	no image	no image
GRAPHS						
Ferrous Alloys						
200 - iron nickel						
150-						
E d						
100 -						
50 -						
0			/24			
May10/24			May10/24			
Non-ferrous Meta	als					
9 - copper 8 - tin						
7-						
6- E_5-						
4						
2						
			-			
May10/24			May10/24			
Viscosity @ 40°C			2			
140 130						
120-						
110 Base						
(2000- (2000- (300- (300-)))))))))))))))))))))))))))))))))))						
80-						
70 - Abnormal						
60 42			/24			
May10/24			May10/24			
: WearCheck USA - 5				NW WI	HITE & CO - GR	
: PCA0120595 : : <mark>06195728</mark>	Recei Teste	<b>d</b> : 31	May 2024 May 2024		1060 ROGEF	DUNCAN, S
· : 11057851 • : FLEET	Diagn	iosed : 01	Jun 2024 - Dor	n Baldridge	Contac	US 2933 t: Matt Quinlat



Test Package : FLEET Certificate 12367 To discuss this sample report, contact Customer Service at 1-800-237-1369. \* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

US 29334 Contact: Matt Quinlan mquinlan@nwwhite.com T: (864)905-8506 F:

Submitted By: moved here from NWWGRE - Matt Quinlan