




OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL



Machine Id
925049-370

Component
Diesel Engine

Fluid
PETRO CANADA DURON SHP 15W40 (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

SAMPLE INFORMATION

	method	limit/base	current	history1	history2
Sample Number	Client Info		GFL0121421	GFL0115852	GFL0111082
Sample Date	Client Info		17 May 2024	16 Apr 2024	07 Feb 2024
Machine Age	hrs	Client Info	10749	10684	10510
Oil Age	hrs	Client Info	10749	10684	0
Oil Changed	Client Info		Changed	N/A	N/A
Sample Status			NORMAL	NORMAL	NORMAL

CONTAMINATION

	method	limit/base	current	history1	history2
Fuel	WC Method	>5	<1.0	<1.0	<1.0
Water	WC Method	>0.2	NEG	NEG	NEG
Glycol	WC Method		NEG	NEG	NEG

WEAR METALS

	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m >100	29	26	13
Chromium	ppm	ASTM D5185m >20	2	2	<1
Nickel	ppm	ASTM D5185m >4	<1	0	0
Titanium	ppm	ASTM D5185m	<1	0	0
Silver	ppm	ASTM D5185m >3	<1	0	0
Aluminum	ppm	ASTM D5185m >20	4	4	2
Lead	ppm	ASTM D5185m >40	<1	<1	<1
Copper	ppm	ASTM D5185m >330	2	2	<1
Tin	ppm	ASTM D5185m >15	<1	<1	<1
Vanadium	ppm	ASTM D5185m	0	<1	<1
Cadmium	ppm	ASTM D5185m	0	0	0

ADDITIVES

	method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m 0	12	10	15
Barium	ppm	ASTM D5185m 0	3	2	3
Molybdenum	ppm	ASTM D5185m 60	64	61	60
Manganese	ppm	ASTM D5185m 0	2	1	<1
Magnesium	ppm	ASTM D5185m 1010	924	902	908
Calcium	ppm	ASTM D5185m 1070	1158	1121	1144
Phosphorus	ppm	ASTM D5185m 1150	1090	932	972
Zinc	ppm	ASTM D5185m 1270	1199	1077	1127
Sulfur	ppm	ASTM D5185m 2060	3255	3260	2958

CONTAMINANTS

	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m >25	7	5	4
Sodium	ppm	ASTM D5185m	7	7	4
Potassium	ppm	ASTM D5185m >20	2	0	<1

INFRA-RED




	method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844 >3	0.3	0.4	0.1
Nitration	Abs/cm	*ASTM D7624 >20	8.2	7.3	5.5
Sulfation	Abs/.1mm	*ASTM D7415 >30	20.4	18.9	17.5

FLUID DEGRADATION

	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414 >25	16.8	14.8	13.3
Base Number (BN)	mg KOH/g	ASTM D2896 9.8	7.9	8.7	9.0







OIL ANALYSIS REPORT



PARAMETER	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG

FLUID PROPERTIES	method	limit/base	current	history1	history2
Visc @ 100°C	cSt	ASTM D445	15.4	13.7	13.4

GRAPHS



Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : GFL0121421 **Received** : 31 May 2024
Lab Number : 06196298 **Tested** : 03 Jun 2024
Unique Number : 11058421 **Diagnosed** : 03 Jun 2024 - Wes Davis
Test Package : FLEET

GFL Environmental - 868 - Childersburg Fines Hauling (Alpine)
 13737 Plant Rd
 Childersburg, AL
 US 35044
 Contact: JONATHAN WILLIAMS
 jonathan.williams@gflenv.com

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)