


# **OIL ANALYSIS REPORT**



**NORMAL** 



Machine Id 2126912

**Diesel Engine** 

PETRO CANADA DURON SHP 10W30 (--- G

### DIAGNOSIS

#### Recommendation

Resample at the next service interval to monitor. Please specify the component make and model with your next sample.

All component wear rates are normal.

## Contamination

There is no indication of any contamination in the oil.


#### Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.


QTS)		Jar	2024	Mar2024 May20	24	
SAMPLE INFORI	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		PCA0124262	PCA0114822	PCA0114800
Sample Date		Client Info		23 May 2024	17 Mar 2024	22 Jan 2024
Machine Age	mls	Client Info		142717	120216	103162
Oil Age	mls	Client Info		20000	40000	20000
Oil Changed		Client Info		Not Changd	Changed	Changed
Sample Status				NORMAL	NORMAL	NORMAL
CONTAMINAT	ION	method	limit/base	current	history1	history2
Fuel		WC Method	>5	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
WEAR METAL	S	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>100	12	24	14
Chromium	ppm	ASTM D5185m	>20	0	<1	<1
Nickel	ppm	ASTM D5185m	>4	0	1	2
Titanium	ppm	ASTM D5185m		14	8	4
Silver	ppm	ASTM D5185m	>3	0	<1	<1
Aluminum	ppm	ASTM D5185m	>20	3	5	5
Lead	ppm	ASTM D5185m	>40	0	0	2
Copper	ppm	ASTM D5185m	>330	8	26	21
Tin	ppm	ASTM D5185m	>15	0	1	1
Vanadium	ppm	ASTM D5185m		<1	0	<1
Cadmium	ppm	ASTM D5185m		0	0	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	2	0	5	10
Barium	ppm	ASTM D5185m	0	0	0	0
Molybdenum	ppm	ASTM D5185m	50	47	56	54
Manganese	ppm	ASTM D5185m	0	<1	<1	<1
Magnesium	ppm	ASTM D5185m	950	809	867	865
Calcium	ppm	ASTM D5185m	1050	1304	1167	1057
Phosphorus	ppm	ASTM D5185m	995	1045	920	1053
Zinc	ppm	ASTM D5185m	1180	1211	1189	1234
Sulfur	ppm	ASTM D5185m	2600	3606	3174	3173
CONTAMINAN		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	2	6	5
Sodium	ppm	ASTM D5185m	00	2	1	2
Potassium	ppm	ASTM D5185m	>20	5	9	9
INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844	>3	0.4	0.6	0.4
Nitration	Abs/cm	*ASTM D7624	>20	8.9	9.8	8.5
Sulfation	Abs/.1mm	*ASTM D7415	>30	19.7	21.7	19.5
FLUID DEGRA	DATION	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414	>25	15.3	17.3	15.5
Base Number (BN)	mg KOH/g	ASTM D2896		7.2	6.1	7.3




# **OIL ANALYSIS REPORT**




Base Nur	mber		
7.0			
7.0 6.0 5.0 5.0 4.0 3.0 2.0		-	
₹5.0+			
a 4.0			
₩ 3.0 ·			
왕 2.0 -			<del>-</del>
1.0			
0.0			
Jan22/24		7/2	100
Jan		Marl7/	W








FLUID PROP	ERHES	method				history2
Visc @ 100°C	cSt	ASTM D445	12.00	11.1	11.3	11.3

## **GRAPHS**













Certificate 12367

Laboratory Sample No. **Lab Number** : 06197275 Unique Number : 11059398

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 : PCA0124262

Test Package : FLEET

To discuss this sample report, contact Customer Service at 1-800-237-1369.

Received : 03 Jun 2024 **Tested** 

: 03 Jun 2024 Diagnosed

: 03 Jun 2024 - Wes Davis

US 21802 Contact: RICHARD O'NEAL richard.oneal@perdue.com T: (410)543-3628

**PERDUE FARMS - SALISBURY** 

7036 ZION CHURCH ROAD

SALISBURY, MD

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

F: (410)341-2164 Contact/Location: RICHARD O'NEAL - PERSALMD