




OIL ANALYSIS REPORT

Sample Rating Trend



GLYCOL



Machine Id
821046-101308

Component
Diesel Engine

Fluid
PETRO CANADA DURON SHP 15W40 (--- GAL)

DIAGNOSIS

Recommendation

No corrective action is recommended at this time. Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

Sodium and/or potassium levels are high. Test for glycol is negative.

Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

SAMPLE INFORMATION

	method	limit/base	current	history1	history2
Sample Number	Client Info		GFL0118480	GFL0118488	GFL0104985
Sample Date	Client Info		04 Jun 2024	04 Apr 2024	04 Mar 2024
Machine Age	hrs	Client Info	0	0	7848
Oil Age	hrs	Client Info	0	0	0
Oil Changed	Client Info		N/A	Not Changd	Not Changd
Sample Status			ABNORMAL	NORMAL	NORMAL

CONTAMINATION

	method	limit/base	current	history1	history2
Fuel	WC Method	>5	<1.0	<1.0	<1.0
Water	WC Method	>0.2	NEG	NEG	NEG

WEAR METALS

	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m >100	31	11	31
Chromium	ppm	ASTM D5185m >20	<1	<1	<1
Nickel	ppm	ASTM D5185m >4	<1	0	0
Titanium	ppm	ASTM D5185m	<1	0	0
Silver	ppm	ASTM D5185m >3	0	0	0
Aluminum	ppm	ASTM D5185m >20	7	3	11
Lead	ppm	ASTM D5185m >40	<1	<1	0
Copper	ppm	ASTM D5185m >330	10	<1	<1
Tin	ppm	ASTM D5185m >15	<1	0	1
Vanadium	ppm	ASTM D5185m	0	<1	0
Cadmium	ppm	ASTM D5185m	0	0	0

ADDITIVES

	method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m 0	<1	0	<1
Barium	ppm	ASTM D5185m 0	0	0	0
Molybdenum	ppm	ASTM D5185m 60	72	63	62
Manganese	ppm	ASTM D5185m 0	<1	0	<1
Magnesium	ppm	ASTM D5185m 1010	943	944	1084
Calcium	ppm	ASTM D5185m 1070	1104	1087	1192
Phosphorus	ppm	ASTM D5185m 1150	1151	1003	1036
Zinc	ppm	ASTM D5185m 1270	1266	1171	1334
Sulfur	ppm	ASTM D5185m 2060	3282	3371	2925

CONTAMINANTS

	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m >25	11	4	5
Sodium	ppm	ASTM D5185m	▲ 60	15	13
Potassium	ppm	ASTM D5185m >20	▲ 58	17	23
Glycol	%	*ASTM D2982	NEG	NEG	NEG

INFRA-RED

	method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844 >3	0.6	0.3	1
Nitration	Abs/cm	*ASTM D7624 >20	9.4	6.5	9.0
Sulfation	Abs/.1mm	*ASTM D7415 >30	20.6	18.3	21.1


FLUID DEGRADATION

	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414 >25	16.0	13.9	16.4
Base Number (BN)	mg KOH/g	ASTM D2896 9.8	8.2	8.9	7.8




OIL ANALYSIS REPORT


FT-IR (Direct Trend)




Glycol Contamination



Viscosity @ 100°C



Glycol Contamination




VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG


FLUID PROPERTIES	method	limit/base	current	history1	history2
Visc @ 100°C	cSt	ASTM D445	15.4	13.7	13.5

GRAPHS


Ferrous Alloys




Non-ferrous Metals



Viscosity @ 100°C



Base Number



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513

Sample No. : GFL0118480

Lab Number : 06202308

Unique Number : 11069769

Test Package : FLEET (Additional Tests: Glycol)

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Received : 06 Jun 2024

Tested : 11 Jun 2024

Diagnosed : 11 Jun 2024 - Jonathan Hester

GFL Environmental - 893 - OK East Hauling

2100 Lilly Street

Seminole, OK

US 74868

Contact: Roger Barlow

rbarlow@gflenv.com

T: (405)204-6183

F: