




# OIL ANALYSIS REPORT

Sample Rating Trend



**NORMAL**



Machine Id

**712027**

Component

**Diesel Engine**

Fluid

**PETRO CANADA DURON SHP 15W40 (--- GAL)**

## DIAGNOSIS

### Recommendation

Resample at the next service interval to monitor.

### Wear

All component wear rates are normal.

### Contamination

There is no indication of any contamination in the oil.

### Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

## SAMPLE INFORMATION

method	limit/base	current	history1	history2	
Sample Number	Client Info	<b>GFL0105080</b>	GFL0105090	GFL0105072	
Sample Date	Client Info	<b>10 Jun 2024</b>	25 Apr 2024	11 Apr 2024	
Machine Age	hrs	Client Info	<b>5942</b>	5669	5525
Oil Age	hrs	Client Info	<b>150</b>	150	150
Oil Changed	Client Info	<b>Not Changed</b>	Not Changed	Not Changed	
Sample Status		<b>NORMAL</b>	NORMAL	NORMAL	

## CONTAMINATION

method	limit/base	current	history1	history2
Fuel	WC Method >5	<b>&lt;1.0</b>	<1.0	<1.0
Water	WC Method >0.2	<b>NEG</b>	NEG	NEG
Glycol	WC Method	<b>NEG</b>	NEG	NEG

## WEAR METALS

method	limit/base	current	history1	history2
Iron	ppm ASTM D5185m >110	<b>10</b>	5	0
Chromium	ppm ASTM D5185m >4	<b>&lt;1</b>	<1	0
Nickel	ppm ASTM D5185m >2	<b>0</b>	0	0
Titanium	ppm ASTM D5185m	<b>0</b>	0	0
Silver	ppm ASTM D5185m >2	<b>0</b>	0	0
Aluminum	ppm ASTM D5185m >25	<b>4</b>	2	1
Lead	ppm ASTM D5185m >45	<b>0</b>	0	0
Copper	ppm ASTM D5185m >85	<b>2</b>	<1	0
Tin	ppm ASTM D5185m >4	<b>&lt;1</b>	<1	0
Vanadium	ppm ASTM D5185m	<b>0</b>	<1	0
Cadmium	ppm ASTM D5185m	<b>0</b>	0	0

## ADDITIVES

method	limit/base	current	history1	history2
Boron	ppm ASTM D5185m 0	<b>&lt;1</b>	2	<1
Barium	ppm ASTM D5185m 0	<b>0</b>	0	0
Molybdenum	ppm ASTM D5185m 60	<b>57</b>	60	52
Manganese	ppm ASTM D5185m 0	<b>&lt;1</b>	<1	0
Magnesium	ppm ASTM D5185m 1010	<b>886</b>	954	861
Calcium	ppm ASTM D5185m 1070	<b>1035</b>	1076	987
Phosphorus	ppm ASTM D5185m 1150	<b>1019</b>	1060	970
Zinc	ppm ASTM D5185m 1270	<b>1196</b>	1281	1118
Sulfur	ppm ASTM D5185m 2060	<b>3343</b>	3756	3126

## CONTAMINANTS

method	limit/base	current	history1	history2
Silicon	ppm ASTM D5185m >30	<b>4</b>	2	2
Sodium	ppm ASTM D5185m	<b>6</b>	20	<1
Potassium	ppm ASTM D5185m >20	<b>6</b>	28	0

## INFRA-RED

method	limit/base	current	history1	history2
Soot %	% *ASTM D7844 >3	<b>0.2</b>	0.1	0.1
Nitration	Abs/cm *ASTM D7624 >20	<b>7.5</b>	6.0	5.2
Sulfation	Abs/.1mm *ASTM D7415 >30	<b>18.5</b>	17.9	17.8


## FLUID DEGRADATION

method	limit/base	current	history1	history2
Oxidation	Abs/.1mm *ASTM D7414 >25	<b>14.7</b>	13.9	13.5
Base Number (BN)	mg KOH/g ASTM D2896 9.8	<b>8.0</b>	8.3	8.7




# OIL ANALYSIS REPORT


FT-IR (Direct Trend)



Base Number



Viscosity @ 100°C




VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG


FLUID PROPERTIES	method	limit/base	current	history1	history2
Visc @ 100°C	cSt	ASTM D445	15.4	13.0	13.4

## GRAPHS


Ferrous Alloys




Non-ferrous Metals



Viscosity @ 100°C



Base Number



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513  
 Sample No. : GFL0105080  
 Lab Number : 06209782  
 Unique Number : 11082646  
 Test Package : FLEET

GFL Environmental - 821 - Ozarks Hauling  
 33924 Olath Drive  
 Lebanon, MO  
 US 65536

Contact: Landen Johnson  
 landen.johnson@gflenv.com  
 T: (417)664-0010

To discuss this sample report, contact Customer Service at 1-800-237-1369.

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

F: