




OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL



Area
(ML7044)
Machine Id
AUTOCAR 832005
Component
Natural Gas Engine
Fluid
{not provided} (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.
Please specify the brand, type, and viscosity of the oil on your next sample.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

SAMPLE INFORMATION		method	limit/base	current	history1	history2
Sample Number	Client Info			GFL0109646	GFL0109601	GFL0109658
Sample Date	Client Info			14 Jun 2024	25 Mar 2024	06 Mar 2024
Machine Age	hrs	Client Info		3110	2558	2456
Oil Age	hrs	Client Info		552	602	500
Oil Changed	Client Info			Changed	Changed	Not Changed
Sample Status				NORMAL	NORMAL	NORMAL

CONTAMINATION		method	limit/base	current	history1	history2
Water	WC Method		>0.1	NEG	NEG	NEG

WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>50	8	20	15
Chromium	ppm	ASTM D5185m	>4	<1	2	1
Nickel	ppm	ASTM D5185m	>2	<1	2	<1
Titanium	ppm	ASTM D5185m		0	<1	0
Silver	ppm	ASTM D5185m	>3	0	0	0
Aluminum	ppm	ASTM D5185m	>9	2	2	2
Lead	ppm	ASTM D5185m	>30	0	3	1
Copper	ppm	ASTM D5185m	>35	1	3	2
Tin	ppm	ASTM D5185m	>4	<1	2	<1
Vanadium	ppm	ASTM D5185m		0	<1	<1
Cadmium	ppm	ASTM D5185m		0	<1	0

ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		11	8	10
Barium	ppm	ASTM D5185m		0	<1	0
Molybdenum	ppm	ASTM D5185m		51	72	72
Manganese	ppm	ASTM D5185m		1	2	1
Magnesium	ppm	ASTM D5185m		581	693	704
Calcium	ppm	ASTM D5185m		1631	1984	2080
Phosphorus	ppm	ASTM D5185m		731	985	853
Zinc	ppm	ASTM D5185m		967	1176	1166
Sulfur	ppm	ASTM D5185m		2702	2921	2797




CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>+100	4	8	5
Sodium	ppm	ASTM D5185m		6	4	7
Potassium	ppm	ASTM D5185m	>20	2	2	0

INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844		0	0	0
Nitration	Abs/cm	*ASTM D7624	>20	11.7	13.5	12.2
Sulfation	Abs/.1mm	*ASTM D7415	>30	22.8	26.9	25.4

FLUID DEGRADATION		method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414	>25	18.9	22.1	20.1
Base Number (BN)	mg KOH/g	ASTM D2896		5.4	4.2	4.6







OIL ANALYSIS REPORT



VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.1	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG

FLUID PROPERTIES	method	limit/base	current	history1	history2
Visc @ 100°C	cSt	ASTM D445	14.9	14.9	14.9

GRAPHS



Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : GFL0109646 **Received** : 17 Jun 2024
Lab Number : 06211275 **Tested** : 18 Jun 2024
Unique Number : 11084139 **Diagnosed** : 18 Jun 2024 - Wes Davis
Test Package : FLEET

GFL Environmental - 331 - Columbus
 180 Ada Moore Rd
 Columbus, NC
 US 28722
 Contact: Jason Ashley
 jashley@gflenv.com

To discuss this sample report, contact Customer Service at 1-800-237-1369.
 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)