




OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL



Machine Id

10951

Component

Diesel Engine

Fluid

PETRO CANADA DURON HP 15W40 (8 GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

SAMPLE INFORMATION

	method	limit/base	current	history1	history2
Sample Number	Client Info		GFL0116013	GFL0090011	GFL0089979
Sample Date	Client Info		18 Jun 2024	05 Mar 2024	23 Jan 2024
Machine Age	hrs	Client Info	42782	42782	42782
Oil Age	hrs	Client Info	0	0	42782
Oil Changed	Client Info		Changed	Changed	Changed
Sample Status			NORMAL	MARGINAL	SEVERE

CONTAMINATION

	method	limit/base	current	history1	history2
Fuel	WC Method	>3.0	<1.0	▲ 1.0	▲ 5.4
Water	WC Method	>0.2	NEG	NEG	NEG
Glycol	WC Method		NEG	NEG	NEG

WEAR METALS

	method	limit/base	current	history1	history2	
Iron	ppm	ASTM D5185m	>90	5	3	54
Chromium	ppm	ASTM D5185m	>20	<1	0	2
Nickel	ppm	ASTM D5185m	>2	0	0	0
Titanium	ppm	ASTM D5185m	>2	0	0	<1
Silver	ppm	ASTM D5185m	>2	0	0	0
Aluminum	ppm	ASTM D5185m	>20	2	2	2
Lead	ppm	ASTM D5185m	>40	2	0	2
Copper	ppm	ASTM D5185m	>330	<1	0	2
Tin	ppm	ASTM D5185m	>15	0	0	<1
Vanadium	ppm	ASTM D5185m		0	0	<1
Cadmium	ppm	ASTM D5185m		0	0	0

ADDITIVES

	method	limit/base	current	history1	history2	
Boron	ppm	ASTM D5185m		3	4	2
Barium	ppm	ASTM D5185m		0	0	0
Molybdenum	ppm	ASTM D5185m		56	56	55
Manganese	ppm	ASTM D5185m		<1	0	<1
Magnesium	ppm	ASTM D5185m		952	885	822
Calcium	ppm	ASTM D5185m		1062	1041	965
Phosphorus	ppm	ASTM D5185m		1063	1003	886
Zinc	ppm	ASTM D5185m		1252	1154	1049
Sulfur	ppm	ASTM D5185m		3619	2802	2135

CONTAMINANTS

	method	limit/base	current	history1	history2	
Silicon	ppm	ASTM D5185m	>25	4	4	4
Sodium	ppm	ASTM D5185m		3	2	6
Potassium	ppm	ASTM D5185m	>20	4	0	35

INFRA-RED




	method	limit/base	current	history1	history2	
Soot %	%	*ASTM D7844	>6	0.3	0.2	▲ 8.1
Nitration	Abs/cm	*ASTM D7624	>20	6.2	5.9	33.7
Sulfation	Abs/.1mm	*ASTM D7415	>30	18.1	17.6	44.8

FLUID DEGRADATION

	method	limit/base	current	history1	history2	
Oxidation	Abs/.1mm	*ASTM D7414	>25	13.8	14.0	53.2
Base Number (BN)	mg KOH/g	ASTM D2896	9.8	8.9	9.0	▲ 0.0







OIL ANALYSIS REPORT



VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG

FLUID PROPERTIES	method	limit/base	current	history1	history2
Visc @ 100°C	cSt	ASTM D445	15.6	14.1	14.3 ▲ 15.1

GRAPHS



Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : GFL0116013 **Received** : 19 Jun 2024
Lab Number : 06214467 **Tested** : 20 Jun 2024
Unique Number : 11087331 **Diagnosed** : 20 Jun 2024 - Wes Davis
Test Package : FLEET

GFL Environmental - 018 - Fayetteville
 4621 Marracco Drive
 Hope Mills, NC
 US 28348
 Contact: Robert Carter
 robert.carter@gflenv.com
 T: (910)596-1170
 F:

To discuss this sample report, contact Customer Service at 1-800-237-1369.
 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)