


OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL



Area
Plymouth & Brockton
 Machine Id
11442
 Component
Diesel Engine
 Fluid
PETRO CANADA 15W40 (36 QTS)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

SAMPLE INFORMATION		method	limit/base	current	history1	history2
Sample Number	Client Info			PCA0104607	PCA0104562	PCA0104494
Sample Date	Client Info			29 Jul 2024	19 Jan 2024	13 Dec 2023
Machine Age	mls	Client Info		251313	215365	204112
Oil Age	mls	Client Info		12000	24000	12000
Oil Changed	Client Info			Not Changed	Changed	Not Changed
Sample Status				NORMAL	NORMAL	NORMAL

CONTAMINATION		method	limit/base	current	history1	history2
Fuel	WC Method	>3.0		<1.0	<1.0	<1.0
Water	WC Method	>0.2		NEG	NEG	NEG
Glycol	WC Method			NEG	NEG	NEG

WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>165	12	18	7
Chromium	ppm	ASTM D5185m	>5	<1	1	1
Nickel	ppm	ASTM D5185m	>4	0	0	0
Titanium	ppm	ASTM D5185m	>2	<1	1	0
Silver	ppm	ASTM D5185m	>2	0	0	0
Aluminum	ppm	ASTM D5185m	>20	1	2	2
Lead	ppm	ASTM D5185m	>150	0	0	0
Copper	ppm	ASTM D5185m	>90	2	<1	0
Tin	ppm	ASTM D5185m	>5	0	<1	0
Vanadium	ppm	ASTM D5185m		<1	0	0
Cadmium	ppm	ASTM D5185m		0	0	0

ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		8	7	3
Barium	ppm	ASTM D5185m		0	<1	4
Molybdenum	ppm	ASTM D5185m		59	57	61
Manganese	ppm	ASTM D5185m		<1	<1	0
Magnesium	ppm	ASTM D5185m		961	859	920
Calcium	ppm	ASTM D5185m		1166	997	1048
Phosphorus	ppm	ASTM D5185m		1016	932	984
Zinc	ppm	ASTM D5185m		1241	1156	1216
Sulfur	ppm	ASTM D5185m		3544	2659	3177


CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>35	3	4	0
Sodium	ppm	ASTM D5185m		3	<1	0
Potassium	ppm	ASTM D5185m	>20	1	0	0

INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844	>7.5	1.1	2.6	1.5
Nitration	Abs/cm	*ASTM D7624	>20	7.7	10.3	7.9
Sulfation	Abs/.1mm	*ASTM D7415	>30	19.6	23.9	20.8


FLUID DEGRADATION		method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414	>25	13.9	15.6	14.1
Base Number (BN)	mg KOH/g	ASTM D2896		13.97	8.32	9.51

OIL ANALYSIS REPORT


FT-IR (Direct Trend)



Base Number



Viscosity @ 100°C




PARAMETER	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG


FLUID PROPERTIES	method	limit/base	current	history1	history2
Visc @ 100°C	cSt	ASTM D445	13.9	14.3	14.2

GRAPHS


Iron (ppm)




Lead (ppm)




Aluminum (ppm)




Chromium (ppm)




Copper (ppm)




Silicon (ppm)



Viscosity @ 100°C



Base Number



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513

Sample No. : PCA0104607

Lab Number : 06214934

Unique Number : 11087798

Test Package : MOB 2

Received : 19 Jun 2024

Tested : 20 Jun 2024

Diagnosed : 20 Jun 2024 - Wes Davis

PLYMOUTH & BROCKTON

8 INDUSTRIAL PARK RD

PLYMOUTH, MA

US 02360

Contact: Donald Pelquin

Dpelquin@P-B.com

T: (508)732-6039

F: (508)732-6091

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)