


OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL



Machine Id
FORD 133693

Component
Gasoline Engine

Fluid
PETRO CANADA DURON SHP 10W30 (--- QTS)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

SAMPLE INFORMATION		method	limit/base	current	history1	history2
Sample Number	Client Info			PCA0128867	PCA0118828	PCA0106297
Sample Date	Client Info			12 Jun 2024	14 Feb 2024	09 Oct 2023
Machine Age	mls	Client Info		29319	18532	11907
Oil Age	mls	Client Info		0	0	0
Oil Changed	Client Info			N/A	Changed	Changed
Sample Status				NORMAL	NORMAL	NORMAL

CONTAMINATION		method	limit/base	current	history1	history2
Fuel	WC Method	>4.0		<1.0	<1.0	<1.0
Water	WC Method	>0.2		NEG	NEG	NEG
Glycol	WC Method			NEG	NEG	NEG

WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>150	6	11	12
Chromium	ppm	ASTM D5185m	>20	0	<1	<1
Nickel	ppm	ASTM D5185m	>5	0	0	<1
Titanium	ppm	ASTM D5185m		0	<1	<1
Silver	ppm	ASTM D5185m	>2	0	0	<1
Aluminum	ppm	ASTM D5185m	>40	2	2	6
Lead	ppm	ASTM D5185m	>50	0	0	1
Copper	ppm	ASTM D5185m	>155	1	4	14
Tin	ppm	ASTM D5185m	>10	<1	<1	<1
Vanadium	ppm	ASTM D5185m		0	<1	<1
Cadmium	ppm	ASTM D5185m		0	0	0




ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	2	3	2	3
Barium	ppm	ASTM D5185m	0	0	0	0
Molybdenum	ppm	ASTM D5185m	50	60	58	74
Manganese	ppm	ASTM D5185m	0	2	2	4
Magnesium	ppm	ASTM D5185m	950	942	845	982
Calcium	ppm	ASTM D5185m	1050	1049	990	1125
Phosphorus	ppm	ASTM D5185m	995	985	880	996
Zinc	ppm	ASTM D5185m	1180	1230	1079	1337
Sulfur	ppm	ASTM D5185m	2600	3374	2611	3220

CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>30	6	<1	15
Sodium	ppm	ASTM D5185m	>400	4	2	1
Potassium	ppm	ASTM D5185m	>20	4	0	1

INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844		0.1	0.1	0
Nitration	Abs./cm	*ASTM D7624	>20	11.1	10.3	10.8
Sulfation	Abs./1mm	*ASTM D7415	>30	22.4	21.0	22.5

FLUID DEGRADATION		method	limit/base	current	history1	history2
Oxidation	Abs./1mm	*ASTM D7414	>25	19.9	17.0	18.7
Base Number (BN)	mg KOH/g	ASTM D2896		6.4	6.8	6.2









OIL ANALYSIS REPORT



PARAMETER	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG

FLUID PROPERTIES	method	limit/base	current	history1	history2
Visc @ 100°C	cSt	ASTM D445	12.00	11.24	10.7

GRAPHS



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : PCA0128867 **Received** : 21 Jun 2024
Lab Number : 06216646 **Tested** : 26 Jun 2024
Unique Number : 11089510 **Diagnosed** : 26 Jun 2024 - Jonathan Hester
Test Package : MOB 1 (Additional Tests: TBN)

MILLER TRUCK LEASING #119
 39 INDUSTRIAL AVE
 HASBROUCK HEIGHTS, NJ
 US 07604
 Contact: MIKE LONGETTE
 mlongette@millertransgroup.com

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

F: (201)528-7053